



TELEPHONE: 01207 590055

FAX 01207590059

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
1.47	0.19	1.09	0.058	0.007	0.043	0.01		SEAM	*						
3.00	0.25	2.50	0.118	0.010	0.098	0.02		WELD	*						
3.00	0.31	2.38	0.118	0.012	0.094	0.02		SEAM	*						
3.00	0.40	2.20	0.118	0.016	0.087	0.03		WELD	*						
3.00	0.50	2.00	0.118	0.020	0.079	0.03		WELD	*						
3.00	1.00	1.00	0.118	0.039	0.039	0.05		WELD	*			*			
3.00	1.00	1.00	0.118	0.039	0.039	0.05		SEAM							*
3.18	0.15	2.88	0.125	0.006	0.113	0.01	1/8 OD X .006	SEAM	*		*	*			
3.18	0.20	2.78	0.125	0.008	0.109	0.01	1/8 OD X .008	SEAM			*	*			
3.18	0.25	2.68	0.125	0.010	0.106	0.02	1/8 OD X .010	SEAM	*		*	*			
3.18	0.30	2.58	0.125	0.012	0.102	0.02	1/8 OD X .012	SEAM	*		*	*			
3.18	0.40	2.38	0.125	0.016	0.094	0.03	1/8 OD X .016	WELD	*			*			
3.18	0.40	2.38	0.125	0.016	0.094	0.03	1/8 OD X .016	SEAM	*		*	*			
3.18	0.46	2.26	0.125	0.018	0.089	0.03	1/8 OD X 018	SEAM			*	*			
3.18	0.51	2.16	0.125	0.020	0.085	0.03	1/8 OD X .020	WELD	*						
3.18	0.51	2.16	0.125	0.020	0.085	0.03	1/8 OD X .020	SEAM	*		*	*			*
3.18	0.56	2.06	0.125	0.022	0.081	0.04	1/8 OD X .022	SEAM	*		*	*			
3.18	0.71	1.76	0.125	0.028	0.069	0.04	1/8 OD X .028	SEAM	*		*	*			*
3.18	0.81	1.56	0.125	0.032	0.061	0.05	1/8 OD X .032	WELD	*						
3.18	0.81	1.56	0.125	0.032	0.061	0.05	1/8 OD X .032	SEAM	*		*	*			
3.18	0.91	1.36	0.125	0.036	0.054	0.05	1/8 OD X .036	SEAM	*		*	*			*
3.18	1.22	0.74	0.125	0.048	0.029	0.06	1/8 OD X .048	SEAM	*		*	*			
3.30	0.40	2.50	0.130	0.016	0.098	0.03		SEAM	*						
3.51	0.40	2.71	0.138	0.016	0.107	0.03		WELD	*						
3.51	0.41	2.69	0.138	0.016	0.106	0.03		SEAM	*						
3.51	0.40	2.71	0.138	0.016	0.107	0.03		SEAM			*	*			
3.68	0.34	3.00	0.145	0.013	0.118	0.03		SEAM	*						
3.69	0.41	2.87	0.145	0.016	0.113	0.03		SEAM	*						
3.70	0.20	3.30	0.146	0.008	0.130	0.02		SEAM	*						
3.97	0.25	3.47	0.156	0.010	0.137	0.02	5/32 OD X .010	SEAM	*		*	*			
3.97	0.40	3.17	0.156	0.016	0.125	0.04	5/32 OD X .016	SEAM	*		*	*			
3.97	0.56	2.85	0.156	0.022	0.112	0.05	5/32 OD X .022	SEAM	*		*	*			
3.97	0.71	2.55	0.156	0.028	0.100	0.06	5/32 OD X .028	SEAM	*		*	*			
3.97	0.91	2.15	0.156	0.036	0.085	0.07	5/32 OD X .036	SEAM	*		*	*			
4.00	0.15	3.70	0.157	0.006	0.146	0.01		WELD	*						
4.00	0.35	3.30	0.157	0.014	0.130	0.03		WELD	*						
4.00	0.37	3.26	0.157	0.015	0.128	0.03		SEAM	*						
4.00	0.40	3.20	0.157	0.016	0.126	0.04		WELD	*						
4.00	0.50	3.00	0.157	0.020	0.118	0.04		SEAM			*		*	*	
4.00	1.00	2.00	0.157	0.039	0.079	0.08		WELD	*			*			
4.00	1.00	2.00	0.157	0.039	0.079	0.08		SEAM	*	*	*		*	*	
4.04	0.38	3.28	0.159	0.015	0.129	0.03		SEAM	*						
4.45	0.38	3.69	0.175	0.015	0.145	0.04		SEAM	*						

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
4.50	0.30	3.90	0.177	0.012	0.154	0.03		WELD	*						
4.50	0.50	3.50	0.177	0.020	0.138	0.05		SEAM					*		
4.50	0.75	3.00	0.177	0.030	0.118	0.07		WELD					*		
4.75	0.73	3.29	0.187	0.029	0.130	0.07		SEAM	*						
4.75	0.92	2.91	0.187	0.036	0.115	0.09		SEAM	*						
4.75	1.22	2.31	0.187	0.048	0.091	0.11		SEAM	*						
4.76	0.13	4.50	0.187	0.005	0.177	0.02	3/16 OD X .005	SEAM				*	*		
4.76	0.20	4.36	0.187	0.008	0.172	0.02	3/16 OD X .008	SEAM				*	*		
4.76	0.25	4.26	0.187	0.010	0.168	0.03	3/16 OD X .010	SEAM	*			*	*		
4.76	0.40	3.96	0.187	0.016	0.156	0.04	3/16 OD X .016	SEAM				*	*		
4.76	0.46	3.84	0.187	0.018	0.151	0.05	3/16 OD X .018	SEAM	*						
4.76	0.51	3.74	0.187	0.020	0.147	0.05	3/16 OD X .020	SEAM	*		*	*	*		*
4.76	0.56	3.64	0.187	0.022	0.143	0.06	3/16 OD X .022	SEAM	*		*	*	*		*
4.76	0.71	3.34	0.187	0.028	0.131	0.07	3/16 OD X .028	SEAM	*		*	*	*		*
4.76	0.81	3.14	0.187	0.032	0.124	0.08	3/16 OD X .032	SEAM	*		*	*	*		*
4.76	0.91	2.94	0.187	0.036	0.116	0.09	3/16 OD X .036	SEAM	*		*	*	*		*
4.76	1.22	2.32	0.187	0.048	0.091	0.11	3/16 OD X .048	SEAM	*		*	*	*		*
4.76	1.63	1.50	0.187	0.064	0.059	0.13	3/16 OD X .064	SEAM				*	*		*
4.98	0.46	4.06	0.196	0.018	0.160	0.05		SEAM	*						
5.00	0.20	4.60	0.197	0.008	0.181	0.02		WELD	*						
5.00	0.25	4.50	0.197	0.010	0.177	0.03		WELD	*						
5.00	0.50	4.00	0.197	0.020	0.157	0.06		WELD	*				*		
5.00	0.50	4.00	0.197	0.020	0.157	0.06		SEAM	*		*	*	*	*	*
5.00	0.75	3.50	0.197	0.030	0.138	0.08		SEAM			*	*	*		
5.00	1.00	3.00	0.197	0.039	0.118	0.10		SEAM	*		*	*	*	*	*
5.00	1.00	3.00	0.197	0.039	0.118	0.10		WELD				*			
5.00	1.25	2.50	0.197	0.049	0.098	0.12		SEAM			*	*			
5.00	1.50	2.00	0.197	0.059	0.079	0.13		SEAM			*	*			
5.50	0.45	4.60	0.217	0.018	0.181	0.06		SEAM	*						
5.50	0.50	4.50	0.217	0.020	0.177	0.06		SEAM	*						
5.70	0.05	5.60	0.224	0.002	0.220	0.01		WELD	*						
6.00	0.50	5.00	0.236	0.020	0.197	0.07		WELD	*				*		
6.00	0.50	5.00	0.236	0.020	0.197	0.07		SEAM	*		*	*	*	*	*
6.00	0.60	4.80	0.236	0.024	0.189	0.08		WELD	*						
6.00	0.75	4.50	0.236	0.030	0.177	0.10		SEAM	*		*				
6.00	1.00	4.00	0.236	0.039	0.157	0.13		WELD	*		*	*	*	*	*
6.00	1.00	4.00	0.236	0.039	0.157	0.13		SEAM	*	*	*	*	*	*	*
6.00	1.20	3.60	0.236	0.047	0.142	0.14		SEAM	*		*				
6.00	1.50	3.00	0.236	0.059	0.118	0.17		SEAM	*		*	*	*	*	*
6.00	2.00	2.00	0.236	0.079	0.079	0.20		SEAM	*		*	*	*	*	*
6.35	0.15	6.05	0.250	0.006	0.238	0.02	1/4 OD X .006	SEAM			*	*			
6.35	0.20	5.95	0.250	0.008	0.234	0.03	1/4 OD X .008	SEAM	*						
6.35	0.25	5.85	0.250	0.010	0.230	0.04	1/4 OD X .010	SEAM	*		*	*			
6.35	0.40	5.55	0.250	0.016	0.219	0.06	1/4 OD X .016	SEAM	*		*	*			
6.35	0.51	5.33	0.250	0.020	0.210	0.07	1/4 OD X .020	SEAM	*		*	*			*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
6.35	0.51	5.33	0.250	0.020	0.210	0.07	1/4 OD X .020	WELD				*			
6.35	0.56	5.23	0.250	0.022	0.206	0.08	1/4 OD X .022	SEAM			*	*			
6.35	0.71	4.93	0.250	0.028	0.194	0.10	1/4 OD X .028	SEAM	*		*	*	*	*	*
6.35	0.81	4.73	0.250	0.032	0.186	0.11	1/4 OD X .032	SEAM	*		*	*	*	*	*
6.35	0.91	4.53	0.250	0.036	0.178	0.12	1/4 OD X .036	SEAM	*	*	*	*	*	*	*
6.35	0.91	4.53	0.250	0.036	0.178	0.12	1/4 OD X .036	WELD				*			
6.35	1.02	4.31	0.250	0.040	0.170	0.14	1/4 OD X .040	SEAM	*						
6.35	1.18	3.99	0.250	0.046	0.157	0.15	1/4 OD X .046	WELD				*			
6.35	1.22	3.91	0.250	0.048	0.154	0.16	1/4 OD X .048	SEAM	*	*	*	*	*	*	*
6.35	1.63	3.09	0.250	0.064	0.122	0.19	1/4 OD X .064	SEAM	*		*	*	*	*	*
6.35	2.03	2.29	0.250	0.080	0.090	0.22	1/4 OD X .080	SEAM	*		*	*	*	*	*
6.35	2.39	1.57	0.250	0.094	0.062	0.24	1/4 OD X .094	SEAM			*	*			
7.00	1.00	5.00	0.276	0.039	0.197	0.15		SEAM	*		*	*			
7.00	1.00	5.00	0.276	0.039	0.197	0.15		WELD				*			
7.00	1.50	4.00	0.276	0.059	0.157	0.21		SEAM	*						
7.11	0.10	6.91	0.280	0.004	0.272	0.02		SEAM	*						
7.20	0.60	6.00	0.283	0.024	0.236	0.10		WELD	*						
7.94	0.40	7.14	0.313	0.016	0.281	0.08	5/16 OD X .016	SEAM			*	*			
7.94	0.51	6.92	0.313	0.020	0.272	0.09	5/16 OD X .020	SEAM	*			*			
7.94	0.56	6.82	0.313	0.022	0.269	0.10	5/16 OD X .022	SEAM	*		*	*			
7.94	0.71	6.52	0.313	0.028	0.257	0.13	5/16 OD X .028	SEAM	*		*	*			
7.94	0.81	6.32	0.313	0.032	0.249	0.14	5/16 OD X .032	SEAM			*	*			
7.94	0.91	6.12	0.313	0.036	0.241	0.16	5/16 OD X .036	SEAM	*		*	*			
7.94	1.22	5.50	0.313	0.048	0.217	0.21	5/16 OD X .048	SEAM	*		*	*			
7.94	1.63	4.68	0.313	0.064	0.184	0.26	5/16 OD X .064	SEAM	*		*	*			
7.94	2.03	3.88	0.313	0.080	0.153	0.30	5/16 OD X .080	SEAM			*	*			
7.94	2.39	3.16	0.313	0.094	0.124	0.33	5/16 OD X .094	SEAM			*	*			
8.00	0.50	7.00	0.315	0.020	0.276	0.09		WELD	*			*			
8.00	0.50	7.00	0.315	0.020	0.276	0.09		SEAM	*		*	*	*	*	*
8.00	1.00	6.00	0.315	0.039	0.236	0.18		WELD	*	*	*	*	*	*	*
8.00	1.00	6.00	0.315	0.039	0.236	0.18		SEAM	*	*	*	*	*	*	*
8.00	1.25	5.50	0.315	0.049	0.217	0.21		SEAM			*				
8.00	1.50	5.00	0.315	0.059	0.197	0.24		WELD	*						
8.00	1.50	5.00	0.315	0.059	0.197	0.24		SEAM	*	*	*	*	*	*	*
8.00	2.00	4.00	0.315	0.079	0.157	0.30		SEAM	*	*	*	*	*	*	*
8.00	2.50	3.00	0.315	0.098	0.118	0.34		SEAM			*	*	*		
8.13	0.09	7.95	0.320	0.004	0.313	0.02		SEAM	*						
9.00	0.50	8.00	0.354	0.020	0.315	0.11		WELD				*			
9.00	1.00	7.00	0.354	0.039	0.276	0.20		SEAM	*		*		*		
9.00	1.50	6.00	0.354	0.059	0.236	0.28		SEAM	*			*			
9.35	0.40	8.55	0.368	0.016	0.337	0.09		WELD				*			
9.53	0.51	8.51	0.375	0.020	0.335	0.12	3/8 OD X .020	SEAM	*		*	*	*	*	*
9.53	0.56	8.41	0.375	0.022	0.331	0.13	3/8 OD X .022	SEAM			*				
9.53	0.71	8.11	0.375	0.028	0.319	0.16	3/8 OD X .028	SEAM	*		*	*	*	*	*
9.53	0.81	7.91	0.375	0.032	0.311	0.18	3/8 OD X .032	SEAM	*		*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310
METRIC			IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 2/3 WEEKS)							
MM	MM	MM	INCH	INCH	INCH									
9.53	0.91	7.71	0.375	0.036	0.304	0.20	3/8 OD X .036	SEAM	*	*	*	*	*	*
9.53	1.00	7.53	0.375	0.039	0.296	0.21	3/8 OD X .039	WELD				*		
9.53	1.14	7.25	0.375	0.045	0.285	0.24	3/8 OD X .045	WELD				*		
9.53	1.22	7.09	0.375	0.048	0.279	0.25	3/8 OD X .048	SEAM	*		*	*	*	*
9.53	1.63	6.27	0.375	0.064	0.247	0.32	3/8 OD X .064	SEAM	*		*	*	*	*
9.53	2.03	5.17	0.375	0.080	0.215	0.38	3/8 OD X .080	SEAM			*	*	*	*
9.53	2.39	4.75	0.375	0.094	0.187	0.43	3/8 OD X .094	SEAM			*	*	*	*
9.53	2.64	4.25	0.375	0.104	0.167	0.46	3/8 OD X .104	SEAM			*	*	*	*
9.53	3.18	3.17	0.375	0.125	0.125	0.51	3/8 OD X .125	SEAM			*	*	*	*
10.00	0.50	9.00	0.394	0.020	0.354	0.12		WELD	*					
10.00	0.50	9.00	0.394	0.020	0.354	0.12		SEAM	*		*			*
10.00	1.00	8.00	0.394	0.039	0.315	0.23		WELD	*		*	*	*	*
10.00	1.00	8.00	0.394	0.039	0.315	0.23		SEAM	*	*	*	*	*	*
10.00	1.50	7.00	0.394	0.059	0.276	0.32		WELD	*		*	*	*	*
10.00	1.50	7.00	0.394	0.059	0.276	0.32		SEAM	*	*	*	*	*	*
10.00	2.00	6.00	0.394	0.079	0.236	0.40		SEAM	*	*	*	*	*	*
10.00	2.50	5.00	0.394	0.098	0.197	0.47		SEAM	*	*		*	*	*
10.20	1.00	8.20	0.402	0.039	0.323	0.23		WELD		*				*
10.20	1.00	8.20	0.402	0.039	0.323	0.23		SEAM		*				*
10.20	1.20	7.80	0.402	0.047	0.307	0.27		SEAM						*
10.20	1.60	7.00	0.402	0.063	0.276	0.34		SEAM	*	*	*		*	*
10.20	2.00	6.20	0.402	0.079	0.244	0.41	1/8 ISO	WELD	*			*		*
10.20	2.00	6.20	0.402	0.079	0.244	0.41	1/8 ISO	SEAM	*	*	*	*	*	*
10.20	2.60	5.00	0.402	0.102	0.197	0.49		SEAM		*				*
10.29	1.24	7.81	0.405	0.049	0.307	0.28	1/8 SCH 10	SEAM	*	*	*	*	*	*
10.29	1.73	6.83	0.405	0.068	0.269	0.37	1/8 SCH 40	SEAM	*	*	*	*	*	*
10.29	2.11	5.47	0.405	0.095	0.215	0.48	1/8 SCH 80	WELD	*					*
10.29	2.11	5.47	0.405	0.095	0.215	0.48	1/8 SCH 80	SEAM		*	*	*	*	*
11.00	0.50	10.00	0.433	0.020	0.394	0.13		WELD	*					
11.00	1.00	9.00	0.433	0.039	0.354	0.25		SEAM			*	*	*	*
11.00	1.50	8.00	0.433	0.059	0.315	0.36		SEAM	*			*	*	*
11.00	2.00	7.00	0.433	0.079	0.276	0.45		SEAM	*		*	*	*	*
11.11	0.46	10.19	0.437	0.018	0.401	0.12	7/16 OD X .018	SEAM	*		*	*	*	*
11.11	0.71	9.69	0.437	0.028	0.381	0.18	7/16 OD X .028	SEAM			*	*	*	*
11.11	0.81	9.19	0.437	0.032	0.374	0.21	7/16 OD X .032	SEAM			*	*	*	*
11.11	0.91	9.29	0.437	0.036	0.366	0.23	7/16 OD X .036	SEAM	*		*	*	*	*
11.11	1.22	8.67	0.437	0.048	0.341	0.30	7/16 OD X .048	SEAM	*		*	*	*	*
11.11	1.63	7.85	0.437	0.064	0.309	0.39	7/16 OD X .064	SEAM	*		*	*	*	*
11.11	2.03	7.05	0.437	0.080	0.278	0.46	7/16 OD X .080	SEAM			*	*	*	*
11.11	2.39	6.33	0.437	0.094	0.249	0.52	7/16 OD X .094	SEAM			*	*	*	*
12.00	0.50	11.00	0.472	0.020	0.433	0.14		WELD	*					
12.00	0.50	11.00	0.472	0.020	0.433	0.14		SEAM			*			
12.00	1.00	10.00	0.472	0.039	0.394	0.28		WELD	*	*	*	*	*	*
12.00	1.00	10.00	0.472	0.039	0.394	0.28		SEAM	*	*	*	*	*	*
12.00	1.50	9.00	0.472	0.059	0.354	0.39		WELD	*		*	*	*	*
12.00	1.50	9.00	0.472	0.059	0.354	0.39		SEAM	*	*	*	*	*	*
12.00	2.00	8.00	0.472	0.079	0.315	0.50		WELD	*		*	*	*	*
12.00	2.00	8.00	0.472	0.079	0.315	0.50		SEAM	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
12.00	2.50	7.00	0.472	0.098	0.276	0.59		SEAM	*		*	*	*	*	
12.00	3.00	6.00	0.472	0.118	0.236	0.68		SEAM		*			*	*	
12.00	4.00	4.00	0.472	0.157	0.157	0.80		SEAM					*	*	
12.70	0.25	12.20	0.500	0.010	0.480	0.08	1/2 OD X .010	SEAM	*		*	*			
12.70	0.46	11.78	0.500	0.018	0.464	0.14	1/2 OD X .018	SEAM			*	*			
12.70	0.56	11.58	0.500	0.022	0.456	0.17	1/2 OD X .022	SEAM			*	*			*
12.70	0.71	11.28	0.500	0.028	0.444	0.21	1/2 OD X .028	SEAM	*		*	*			*
12.70	0.91	10.88	0.500	0.036	0.428	0.27	1/2 OD X .036	SEAM	*		*	*			*
12.70	1.22	10.26	0.500	0.048	0.404	0.35	1/2 OD X .048	SEAM	*	*	*	*			*
12.70	1.63	9.44	0.500	0.064	0.372	0.45	1/2 OD X .064	SEAM	*		*	*			*
12.70	2.03	8.64	0.500	0.080	0.340	0.54	1/2 OD X .080	SEAM	*		*	*			*
12.70	2.39	7.92	0.500	0.094	0.312	0.62	1/2 OD X .094	SEAM			*	*			*
12.70	2.64	7.42	0.500	0.104	0.292	0.67	1/2 OD X .104	SEAM	*		*	*			*
12.70	3.18	6.34	0.500	0.125	0.250	0.76	1/2 OD X .125	SEAM	*		*	*			*
13.00	1.00	11.00	0.512	0.039	0.433	0.30		WELD	*				*		
13.00	1.00	11.00	0.512	0.039	0.433	0.30		SEAM	*		*		*		
13.00	1.50	10.00	0.512	0.059	0.394	0.43		WELD	*						
13.00	1.50	10.00	0.512	0.059	0.394	0.43		SEAM	*		*	*	*	*	*
13.00	2.50	8.00	0.512	0.098	0.315	0.66		SEAM	*	*	*				
13.25	2.75	7.75	0.522	0.108	0.305	0.72		SEAM		*					
13.36	2.03	9.30	0.526	0.080	0.366	0.58	1/4 BSP STANDARD	SEAM			*	*			
13.36	2.64	8.08	0.526	0.104	0.318	0.71	1/4 BSP HEAVY	SEAM			*	*			
13.49	3.25	6.99	0.531	0.128	0.275	0.83	1/4 BSP	SEAM					*		
13.50	1.60	10.30	0.531	0.063	0.406	0.48		SEAM	*	*	*		*	*	*
13.50	1.60	10.30	0.531	0.063	0.406	0.48		WELD				*			
13.50	1.80	9.90	0.531	0.071	0.390	0.53		SEAM						*	*
13.50	2.00	9.50	0.531	0.079	0.374	0.58		SEAM	*	*	*		*	*	*
13.50	2.03	9.44	0.531	0.080	0.372	0.58		SEAM				*			
13.50	2.30	8.90	0.531	0.091	0.350	0.65	1/4 ISO	WELD	*	*		*		*	*
13.50	2.30	8.90	0.531	0.091	0.350	0.65	1/4 ISO	SEAM	*	*	*	*	*	*	*
13.50	2.60	8.30	0.531	0.102	0.327	0.71		SEAM			*	*			
13.50	2.90	7.70	0.531	0.114	0.303	0.77		SEAM			*	*		*	
13.50	3.25	7.00	0.531	0.128	0.276	0.83		SEAM			*			*	*
13.70	1.65	10.40	0.539	0.065	0.409	0.50		WELD							*
13.72	1.24	11.24	0.540	0.049	0.443	0.39	1/4SCH5	SEAM	*		*	*			
13.72	1.65	10.42	0.540	0.065	0.410	0.50	1/4SCH10	SEAM	*	*	*	*			*
13.72	1.65	10.42	0.540	0.065	0.410	0.50	1/4SCH10	WELD		*				*	*
13.72	2.24	9.24	0.540	0.088	0.364	0.64	1/4 SCH 40	SEAM	*	*	*	*		*	*
13.72	2.24	9.24	0.540	0.088	0.364	0.64	1/4 SCH 40	WELD		*				*	*
13.72	3.02	7.68	0.540	0.119	0.302	0.81	1/4 SCH 80	SEAM	*	*	*	*		*	*
14.00	1.00	12.00	0.551	0.039	0.472	0.33		WELD	*	*	*	*	*	*	*
14.00	1.00	12.00	0.551	0.039	0.472	0.33		SEAM	*	*	*	*	*	*	*
14.00	1.50	11.00	0.551	0.059	0.433	0.47		WELD	*		*		*		*
14.00	1.50	11.00	0.551	0.059	0.433	0.47		SEAM	*	*	*	*	*	*	*
14.00	2.00	10.00	0.551	0.079	0.394	0.60		WELD	*		*	*	*	*	*



TELEPHONE: 01207 590055

FAX 01207590059

STAINLESS STEEL HOLLOW BARTUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC		IMPERIAL			KGS/MTR		* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
14.00	2.00	1000	0.551	0.079	0.394	0.60		SEAM	*	*	*	*	*	*	*
14.00	2.50	9.00	0.551	0.098	0.354	0.72		SEAM	*		*	*	*	*	
14.00	3.00	8.00	0.551	0.118	0.315	0.83		SEAM	*		*	*	*	*	
14.29	0.71	12.87	0.563	0.028	0.507	0.24	9/16 OD X .028	SEAM			*	*			
14.29	0.91	12A7	0.563	0.036	0A91	0.30	9/16 OD X .036	SEAM	*		*	*			
14.29	1.22	11.85	0.563	0.048	0.467	0A0	9/16 OD X .048	SEAM			*	*			
14.29	1.63	1103	0.563	0.064	0A34	0.52	9/16 OD X .064	SEAM			*	*			
14.29	2.39	9.51	0.563	0.094	0.374	0.71	9/16 OD X .094	SEAM			*	*			
14.29	3.18	7.93	0.563	0.125	0.312	0.88	9/16ODX.125	SEAM			*	*			
15.00	1.00	13.00	0.591	0.039	0.512	0.35		WELD	*		*	*	*		
15.00	1.00	13.00	0.591	0.039	0.512	0.35		SEAM	*	*	*	*	*	*	*
15.00	1.50	12.00	0.591	0.059	0.472	0.51		WELD	*		*	*	*		*
15.00	1.50	12.00	0.591	0.059	0.472	0.51		SEAM	*	*	*	*	*	*	*
15.00	2.00	11.00	0.591	0.079	0.433	0.65		WELD	*		*	*	*		*
15.00	2.00	1100	0.591	0.079	0A33	0.65		SEAM	*	*	*	*	*	*	*
15.00	2.50	10.00	0.591	0.098	0.394	0.78		SEAM			*	*	*		
15.00	3.00	900	0.591	0.118	0.354	0.90		SEAM			*	*	*		
15.00	4.00	700	0.591	0.157	0.276	1.10		SEAM			*	*	*		
15.88	0.25	15.38	0.625	0.010	0.606	0.10	5/8 OD X .010	SEAM			*	*			
15.88	0.71	14A6	0.625	0.028	0.569	0.27	5/8 OD X .028	SEAM	*		*	*	*		*
15.88	0.91	14.06	0.625	0.036	0.554	0.34	5/8 OD X .036	SEAM	*		*	*	*		*
15.88	1.22	13.44	0.625	0.048	0.529	0A5	5/8 OD X .048	SEAM	*		*	*	*		*
15.88	1.63	12.62	0.625	0.064	0A97	0.58	5/8 OD X .064	SEAM	*		*	*	*		*
15.88	2.03	11.82	0.625	0.080	0.465	0.70	5/8 OD X .080	SEAM			*	*	*		*
15.88	2.64	1060	0.625	0.104	0A17	0.88	5/8 OD X .104	SEAM			*	*	*		*
15.88	3.18	9.52	0.625	0.125	0.375	1.01	5/8 OD X .125	SEAM	*		*	*	*		*
15.88	3A0	9.08	0.625	0.134	0.357	1.06	5/8 OD X .134	SEAM			*	*	*		*
15.88	4.78	6.32	0.625	0.188	0.249	1.33	5/8 OD X .188	SEAM			*	*	*		*
16.00	1.00	14.00	0.630	0.039	0.551	0.38		WELD	*	*	*	*	*	*	*
16.00	1.00	14.00	0.630	0.039	0.551	0.38		SEAM	*	*	*	*	*	*	*
16.00	1.20	13.60	0.630	0.047	0.535	0.44		SEAM			*	*	*		*
16.00	1.50	13.00	0.630	0.059	0.512	0.54		WELD	*		*	*	*		*
16.00	1.50	13.00	0.630	0.059	0.512	0.54		SEAM	*	*	*	*	*	*	*
16.00	2.00	12.00	0.630	0.079	0A72	0.70		WELD	*		*	*	*	*	*
16.00	2.00	12.00	0.630	0.079	0.472	0.70		SEAM	*	*	*	*	*	*	*
16.00	2.50	11.00	0.630	0.098	0.433	0.85		SEAM	*		*	*	*	*	*
16.00	3.00	10.00	0.630	0.118	0.394	0.98		SEAM	*		*	*	*	*	*
16.00	3.20	9.60	0.630	0.126	0.378	1.03		SEAM			*	*	*		*
16.00	3.50	9.00	0.630	0.138	0.354	1.10		SEAM			*	*	*		*
16.00	4.00	8.00	0.630	0.157	0.315	1.20		SEAM			*	*	*		*
17.00	1.00	15.00	0.669	0.039	0.591	0A0		WELD	*		*	*	*	*	*
17.00	1.00	15.00	0.669	0.039	0.591	0.40		SEAM	*		*	*	*	*	*
17.00	1.50	14.00	0.669	0.059	0.551	0.58		SEAM	*		*	*	*	*	*
17.00	2.00	13.00	0.669	0.079	0.512	0.75		SEAM			*	*	*	*	*
17.00	3.00	11.00	0.669	0.118	0A33	1.05		SEAM	*		*	*	*	*	*
17.15	1.24	14.67	0.675	0.049	0.578	0.49	3/8 SCH 5	SEAM	*		*	*	*	*	*
17.15	1.65	13.85	0.675	0.065	0.545	0.64	3/8 SCH 10	SEAM	*	*	*	*	*	*	*
17.15	1.65	13.85	0.675	0.065	0.545	0.64	3/8 SCH 10	WELD		*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
17.15	2.31	12.53	0.675	0.091	0.493	0.86	3/8 SCH 40	SEAM	*	*	*	*	*	*	*
17.15	3.20	10.75	0.675	0.126	0.423	1.12	3/8 SCH 80	SEAM	*	*	*	*	*	*	*
17.20	1.60	14.00	0.677	0.063	0.551	0.62		WELD	*	*	*	*	*	*	*
17.20	1.60	14.00	0.677	0.063	0.551	0.62		SEAM	*	*	*	*	*	*	*
17.20	1.80	13.60	0.677	0.071	0.535	0.69		SEAM			*	*	*	*	*
17.20	2.00	13.20	0.677	0.079	0.520	0.76		WELD	*	*	*	*	*	*	*
17.20	2.00	13.20	0.677	0.079	0.520	0.76		SEAM	*	*	*	*	*	*	*
17.20	2.30	12.60	0.677	0.091	0.496	0.86	3/8 ISO	WELD	*	*	*	*	*	*	*
17.20	2.30	12.60	0.677	0.091	0.496	0.86	3/8 ISO	SEAM	*	*	*	*	*	*	*
17.20	2.60	12.00	0.677	0.102	0.472	0.95		SEAM			*	*	*	*	*
17.20	2.90	11.40	0.677	0.114	0.449	1.04		SEAM			*	*	*	*	*
17.20	3.20	10.80	0.677	0.126	0.425	1.12		SEAM			*	*	*	*	*
17.46	0.91	15.64	0.687	0.036	0.616	0.38	11/16 OD X .036	SEAM	*		*	*	*	*	*
17.46	1.63	14.20	0.687	0.064	0.559	0.65	11/16 OD X .064	SEAM			*	*	*	*	*
17.46	2.39	12.68	0.687	0.094	0.499	0.90	11/16 OD X .094	SEAM			*	*	*	*	*
17.46	3.05	11.36	0.687	0.120	0.447	1.10	11/16ODX.120	SEAM			*	*	*	*	*
17.47	2.34	12.79	0.688	0.092	0.504	0.89	3/8 BSP	SEAM					*	*	*
18.00	1.00	16.00	0.709	0.039	0.630	0.43		WELD	*	*	*	*	*	*	*
18.00	1.00	16.00	0.709	0.039	0.630	0.43		SEAM	*	*	*	*	*	*	*
18.00	1.50	15.00	0.709	0.059	0.591	0.62		WELD	*	*	*	*	*	*	*
18.00	1.50	15.00	0.709	0.059	0.591	0.62		SEAM	*	*	*	*	*	*	*
18.00	2.00	14.00	0.709	0.079	0.551	0.80		WELD	*	*	*	*	*	*	*
18.00	2.00	14.00	0.709	0.079	0.551	0.80		SEAM	*	*	*	*	*	*	*
18.00	2.50	13.00	0.709	0.098	0.512	0.97		SEAM	*	*	*	*	*	*	*
18.00	3.00	12.00	0.709	0.118	0.472	1.13		SEAM	*	*	*	*	*	*	*
18.00	3.50	11.00	0.709	0.138	0.433	1.27		SEAM			*	*	*	*	*
18.00	4.00	10.00	0.709	0.157	0.394	1.40		SEAM			*	*	*	*	*
18.00	5.00	8.00	0.709	0.197	0.315	1.63		SEAM			*	*	*	*	*
19.00	1.50	16.00	0.748	0.059	0.630	0.66		WELD	*			*	*	*	*
19.00	1.50	16.00	0.748	0.059	0.630	0.66		SEAM			*	*	*	*	*
19.00	2.00	15.00	0.748	0.079	0.591	0.85		SEAM			*	*	*	*	*
19.05	0.56	17.93	0.750	0.022	0.706	0.26	3/4 OD X .022	SEAM	*		*	*	*	*	*
19.05	0.71	17.63	0.750	0.028	0.694	0.33	3/4 OD X .028	SEAM	*		*	*	*	*	*
19.05	0.91	17.23	0.750	0.036	0.678	0.41	3/4 OD X .036	SEAM	*		*	*	*	*	*
19.05	1.22	16.61	0.750	0.048	0.654	0.54	3/4 OD X .048	SEAM	*		*	*	*	*	*
19.05	1.63	15.79	0.750	0.064	0.622	0.71	3/4 OD X .064	WELD	*		*	*	*	*	*
19.05	1.63	15.79	0.750	0.064	0.622	0.71	3/4 OD X .064	SEAM	*	*	*	*	*	*	*
19.05	2.03	14.99	0.750	0.080	0.590	0.87	3/4 OD X .080	SEAM	*	*	*	*	*	*	*
19.05	2.64	13.77	0.750	0.104	0.542	1.08	3/4 OD X .104	SEAM	*	*	*	*	*	*	*
19.05	3.18	12.69	0.750	0.125	0.500	1.26	3/4 OD X .125	SEAM	*	*	*	*	*	*	*
19.05	4.78	9.49	0.750	0.188	0.374	1.71	3/4 OD X .188	SEAM	*	*	*	*	*	*	*
20.00	1.00	18.00	0.787	0.039	0.709	0.48		WELD	*	*	*	*	*	*	*
20.00	1.00	18.00	0.787	0.039	0.709	0.48		SEAM	*	*	*	*	*	*	*
20.00	1.25	17.50	0.787	0.049	0.689	0.59		WELD	*	*	*	*	*	*	*
20.00	1.50	17.00	0.787	0.059	0.669	0.69		WELD	*	*	*	*	*	*	*
20.00	1.50	17.00	0.787	0.059	0.669	0.69		SEAM	*	*	*	*	*	*	*
20.00	1.60	16.80	0.787	0.063	0.661	0.74		WELD			*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC		IMPERIAL			KGS/MTR		* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
2000	2.00	16.00	0.787	0.079	0.630	0.90		WELD	*		*	*	*		
20.00	2.00	16.00	0.787	0.079	0.630	0.90		SEAM	*	*	*	*	*	*	*
20.00	2.50	15.00	0.787	0.098	0.591	1.10		SEAM	*	*	*	*	*	*	*
2000	3.00	14.00	0.787	0.118	0.551	1.28		SEAM	*		*	*	*	*	
20.00	3.50	13.00	0.787	0.138	0.512	1.45		SEAM	*		*	*	*	*	
20.00	4.00	12.00	0.787	0.157	0.472	1.60		SEAM	*		*	*	*	*	
20.00	5.00	10.00	0.787	0.197	0.394	1.88		SEAM	*		*	*	*	*	
20.00	6.00	8.00	0.787	0.236	0.315	2.10		SEAM	*		*	*	*	*	
<hr/>															
20.64	1.22	18.20	0.813	0.048	0.717	0.59	13/16 OD X .048	SEAM	*		*	*			
2064	1.63	17.38	0.813	0.064	0.684	0.78	13/16 OD X .064	SEAM	*		*	*			
<hr/>															
2100	1.50	1800	0.827	0.059	0.709	0.73		SEAM					*		
21.00	3.00	15.00	0.827	0.118	0.591	1.35		SEAM	*						
<hr/>															
21.34	1.65	1804	0.840	0.065	0.710	0.81	1/2 SCH 5	WELD	*	*	*	*	*	*	*
21.34	1.65	18.04	0.840	0.065	0.710	0.81	1/2 SCH 5	SEAM	*	*	*	*	*	*	*
21.34	2.00	17.34	0.840	0.079	0.683	0.97		WELD	*	*	*	*	*	*	*
21.34	2.00	17.34	0.840	0.079	0.683	0.97		SEAM	*	*	*	*	*	*	*
2134	2.11	1712	0.840	0.083	0.674	1.02	1/2 SCH 10	SEAM	*	*	*	*	*	*	*
21.34	2.11	17.12	0.840	0.083	0.674	1.02	1/2 SCH 10	WELD	*	*	*	*	*	*	*
21.34	2.60	16.14	0.840	0.102	0.635	1.22		WELD	*	*	*	*	*	*	*
21.34	2.60	16.14	0.840	0.102	0.635	1.22		SEAM	*	*	*	*	*	*	*
21.34	2.77	15.80	0.840	0.109	0.622	1.29	1/2 SCH 40	SEAM	*	*	*	*	*	*	*
21.34	2.77	15.80	0.840	0.109	0.622	1.29	1/2 SCH 40	WELD	*	*	*	*	*	*	*
21.34	2.90	15.54	0.840	0.114	0.612	1.34		SEAM	*	*	*	*	*	*	*
21.34	3.20	14.94	0.840	0.126	0.588	1.45		SEAM	*	*	*	*	*	*	*
21.34	3.73	13.88	0.840	0.147	0.546	1.64	1/2 SCH 80	SEAM	*	*	*	*	*	*	*
21.34	4.78	1178	0.840	0.188	0.464	1.98	1/2 SCH 160	SEAM	*	*	*	*	*	*	*
21.34	7.47	6.40	0.840	0.294	0.252	2.59	1/2 XXS	SEAM	*	*	*	*	*	*	*
<hr/>															
21.41	3.25	14.91	0.843	0.128	0.587	1.48	1/2 ISO HEAVY	SEAM			*	*	*	*	*
<hr/>															
21.44	2.64	16.16	0.844	0.104	0.636	1.24	1/2 BSP	SEAM			*	*	*	*	*
<hr/>															
22.00	1.00	20.00	0.866	0.039	0.787	0.53		WELD	*	*	*	*	*	*	*
22.00	1.00	20.00	0.866	0.039	0.787	0.53		SEAM	*	*	*	*	*	*	*
22.00	1.50	1900	0.866	0.059	0.748	0.77		WELD	*	*	*	*	*	*	*
22.00	1.50	19.00	0.866	0.059	0.748	0.77		SEAM	*	*	*	*	*	*	*
22.00	2.00	18.00	0.866	0.079	0.709	1.00		WELD	*	*	*	*	*	*	*
22.00	2.00	18.00	0.866	0.079	0.709	1.00		SEAM	*	*	*	*	*	*	*
22.00	2.50	17.00	0.866	0.098	0.669	1.22		SEAM	*	*	*	*	*	*	*
22.00	3.00	16.00	0.866	0.118	0.630	1.43		SEAM	*	*	*	*	*	*	*
22.00	4.00	14.00	0.866	0.157	0.551	1.80		SEAM	*	*	*	*	*	*	*
22.00	5.00	12.00	0.866	0.197	0.472	2.13		SEAM	*	*	*	*	*	*	*
22.00	6.00	10.00	0.866	0.236	0.394	2.40		SEAM	*	*	*	*	*	*	*
<hr/>															
22.23	0.91	20.41	0.875	0.036	0.804	0.49	7/8 OD X .036	SEAM	*	*	*	*	*	*	*
22.23	1.22	19.79	0.875	0.048	0.779	0.64	7/8 OD X .048	SEAM	*	*	*	*	*	*	*
22.23	1.63	18.97	0.875	0.064	0.747	0.84	7/8 OD X .064	SEAM	*	*	*	*	*	*	*
22.23	2.03	18.17	0.875	0.080	0.715	1.03	7/8 OD X .080	SEAM	*	*	*	*	*	*	*
22.23	2.64	16.95	0.875	0.104	0.667	1.30	7/8 OD X .104	SEAM	*	*	*	*	*	*	*
22.23	3.18	15.87	0.875	0.125	0.625	1.52	7/8 OD X .125	SEAM	*	*	*	*	*	*	*
22.23	4.78	12.67	0.875	0.188	0.499	2.09	7/8 OD X .188	SEAM	*	*	*	*	*	*	*



TELEPHONE: 01207 590055

FAX 01207590059

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
23.00	1.50	20.00	0.906	0.059	0.787	0.81		WELD	*	*	*	*	*	*	*
23.00	1.50	20.00	0.906	0.059	0.787	0.81		SEAM	*	*	*	*	*	*	*
23.00	3.87	15.26	0.906	0.152	0.601	1.85		SEAM				*			
24.00	1.00	22.00	0.945	0.039	0.866	0.58		SEAM	*		*		*		
24.00	1.50	21.00	0.945	0.059	0.827	0.85		SEAM			*				
24.00	2.00	20.00	0.945	0.079	0.787	1.10		WELD	*						
24.00	2.00	20.00	0.945	0.079	0.787	1.10		SEAM	*	*	*		*	*	*
24.00	3.00	18.00	0.945	0.118	0.709	1.58		SEAM					*		
24.00	3.50	17.00	0.945	0.138	0.669	1.80		SEAM			*		*		
24.00	4.00	16.00	0.945	0.157	0.630	2.00		SEAM	*		*		*		
24.00	5.00	14.00	0.945	0.197	0.551	2.38		SEAM					*		
24.00	7.00	10.00	0.945	0.276	0.394	2.98		SEAM			*		*		
25.00	1.00	23.00	0.984	0.039	0.906	0.60		WELD	*	*	*		*	*	*
25.00	1.00	23.00	0.984	0.039	0.906	0.60		SEAM	*	*	*	*	*	*	*
25.00	1.20	22.60	0.984	0.047	0.890	0.72		SEAM			*				
25.00	1.50	22.00	0.984	0.059	0.866	0.88		WELD	*		*	*	*		
25.00	1.50	22.00	0.984	0.059	0.866	0.88		SEAM	*	*	*	*	*	*	*
25.00	2.00	21.00	0.984	0.079	0.827	1.15		WELD	*		*	*	*		*
25.00	2.00	21.00	0.984	0.079	0.827	1.15		SEAM	*	*	*	*	*	*	*
25.00	2.50	20.00	0.984	0.098	0.787	1.41		WELD	*		*		*		
25.00	2.50	20.00	0.984	0.098	0.787	1.41		SEAM	*	*	*	*	*	*	*
25.00	3.00	19.00	0.984	0.118	0.748	1.65		SEAM	*		*	*	*	*	*
25.00	3.20	18.60	0.984	0.126	0.732	1.75		SEAM					*		
25.00	3.50	18.00	0.984	0.138	0.709	1.88		SEAM			*		*		
25.00	4.00	17.00	0.984	0.157	0.669	2.10		SEAM			*	*	*	*	*
25.00	5.00	15.00	0.984	0.197	0.591	2.50		SEAM	*		*	*	*		
25.00	6.00	13.00	0.984	0.236	0.512	2.85		SEAM	*						
25.40	0.71	23.98	1.000	0.028	0.944	0.44	1 OD X .028	SEAM			*	*			
25.40	0.91	23.58	1.000	0.036	0.928	0.56	1 OD X .036	SEAM	*		*	*			
25.40	1.22	22.96	1.000	0.048	0.904	0.74	1 OD X .048	WELD	*			*			
25.40	1.22	22.96	1.000	0.048	0.904	0.74	1 OD X .048	SEAM	*		*	*			
25.40	1.63	22.14	1.000	0.064	0.872	0.97	1 OD X .064	WELD	*			*			
25.40	1.63	22.14	1.000	0.064	0.872	0.97	1 OD X .064	SEAM	*	*	*	*	*		*
25.40	2.03	21.34	1.000	0.080	0.840	1.19	1 OD X .080	SEAM	*		*	*			
25.40	2.11	21.18	1.000	0.083	0.834	1.23	1 OD X .083	SEAM		*					*
25.40	2.41	20.58	1.000	0.095	0.810	1.39	1 OD X .095	SEAM		*					
25.40	2.64	20.12	1.000	0.104	0.792	1.50	1 OD X .104	SEAM	*		*	*			
25.40	2.77	19.86	1.000	0.109	0.782	1.57	1 OD X .109	SEAM		*					
25.40	3.18	19.04	1.000	0.125	0.750	1.77	1 OD X .125	SEAM	*		*	*			
25.40	4.78	15.84	1.000	0.188	0.624	2.47	1 OD X .188	SEAM			*	*			
25.40	6.35	12.70	1.000	0.250	0.500	3.03	1 OD X .250	SEAM				*	*		
25.40	9.53	6.34	1.000	0.375	0.250	3.79	1 OD X .375	SEAM			*	*			
26.00	3.00	20.00	1024	0.118	0.787	1.73		SEAM			*				
26.00	3.00	20.00	1024	0.118	0.787	1.73		WELD							*
26.40	3.80	18.80	1.039	0.150	0.740	2.15		SEAM			*		*		
26.67	1.65	23.37	1.050	0.065	0.920	1.03	3/4 SCH 5	SEAM	*	*	*	*	*	*	*
26.67	1.65	23.37	1.050	0.065	0.920	1.03	3/4 SCH 5	WELD		*	*				*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310	
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
26.67	2.11	22.45	1.050	0.083	0.884	1.30	3/4SCH10	SEAM	*	*	*	*	*	*	
26.67	2.11	22.45	1.050	0.083	0.884	1.30	3/4SCH 10	WELD		*	*		*	*	
26.67	2.87	20.93	1.050	0.113	0.824	1.71	3/4 SCH 40	SEAM	*	*	*	*	*	*	
26.67	2.87	20.93	1.050	0.113	0.824	1.71	3/4 SCH 40	WELD		*	*		*	*	
26.67	3.91	18.85	1.050	0.154	0.742	2.23	3/4 SCH 80	SEAM	*	*	*	*	*	*	
26.67	5.56	15.55	1.050	0.219	0.612	2.94	3/4 SCH 160	SEAM	*	*	*	*	*	*	
26.67	7.82	11.03	1.050	0.308	0.434	3.69	3/4 XXS	SEAM		*	*	*	*	*	
26.90	1.60	23.70	1.059	0.063	0.933	1.01		WELD	*	*	*		*	*	
26.90	1.60	23.70	1.059	0.063	0.933	1.01		SEAM	*	*	*	*	*	*	
26.90	2.00	22.90	1.059	0.079	0.902	1.25		WELD	*	*	*		*	*	
26.90	2.00	22.90	1.059	0.079	0.902	1.25		SEAM	*	*	*		*	*	
26.90	2.30	22.30	1.059	0.091	0.878	1.42		SEAM			*		*	*	
26.90	2.60	21.70	1.059	0.102	0.854	1.58	3/4 ISO	WELD	*	*	*	*	*	*	
26.90	2.60	21.70	1.059	0.102	0.854	1.58	3/4 ISO	SEAM	*	*	*	*	*	*	
26.90	2.90	21.10	1.059	0.114	0.831	1.74		SEAM			*				
26.90	3.20	20.50	1.059	0.126	0.807	1.90		SEAM	*		*	*	*	*	
26.90	3.50	19.90	1.059	0.138	0.783	2.05		SEAM				*			
26.90	4.00	18.90	1.059	0.157	0.744	2.29		SEAM			*		*		
27.00	1.00	25.00	1.063	0.039	0.984	0.65		SEAM			*				
27.00	3.00	21.00	1.063	0.118	0.827	1.80		SEAM	*						
27.00	3.50	20.00	1.063	0.138	0.787	2.06		SEAM	*	*					
27.00	4.00	19.00	1.063	0.157	0.748	2.30		SEAM	*		*		*		
28.00	1.00	26.00	1.102	0.039	1.024	0.68		WELD	*			*	*		
28.00	1.00	26.00	1.102	0.039	1.024	0.68		SEAM	*		*	*	*		
28.00	1.50	25.00	1.102	0.059	0.984	1.00		WELD	*	*	*	*	*	*	
28.00	1.50	25.00	1.102	0.059	0.984	1.00		SEAM	*	*	*	*	*	*	
28.00	2.00	24.00	1.102	0.079	0.945	1.30		WELD	*		*		*		
28.00	2.00	24.00	1.102	0.079	0.945	1.30		SEAM	*	*	*	*	*	*	
28.00	2.50	23.00	1.102	0.098	0.906	1.60		SEAM		*	*				
28.00	3.00	22.00	1.102	0.118	0.866	1.88		SEAM			*	*	*		
28.00	3.00	22.00	1.102	0.118	0.866	1.88		WELD						*	
28.00	3.50	21.00	1.102	0.138	0.827	2.15		SEAM			*		*		
28.00	4.00	20.00	1.102	0.157	0.787	2.40		SEAM			*		*		
28.00	5.00	18.00	1.102	0.197	0.709	2.88		SEAM	*		*	*	*		
28.58	0.91	26.76	1.125	0.036	1.054	0.63	1.118 OD X .036	SEAM	*		*	*			
28.58	1.22	26.14	1.125	0.048	1.029	0.84	1.118 OD X .048	SEAM			*	*			
28.58	1.63	25.32	1.125	0.064	0.997	1.10	1.118 OD X .064	SEAM	*		*	*			
28.58	2.03	24.52	1.125	0.080	0.965	1.35	1.118 OD X .080	SEAM			*	*			
28.58	3.18	22.22	1.125	0.125	0.875	2.02	1.118 OD X .125	SEAM		*		*			
28.58	4.78	19.02	1.125	0.188	0.749	2.85	1.118 OD X .188	SEAM			*	*			
28.58	6.35	15.88	1.125	0.250	0.625	3.53	1.118 OD X .250	SEAM				*			
29.00	2.00	25.00	1.142	0.079	0.984	1.35		SEAM					*		
30.00	1.00	28.00	1.181	0.039	1.102	0.73		WELD	*		*		*		
30.00	1.00	28.00	1.181	0.039	1.102	0.73		SEAM	*		*	*	*		
30.00	1.50	27.00	1.181	0.059	1.063	1.07		WELD	*	*	*	*	*	*	
30.00	1.50	27.00	1.181	0.059	1.063	1.07		SEAM	*	*	*	*	*	*	
30.00	2.00	26.00	1.181	0.079	1.024	1.40		WELD	*		*	*	*	*	
30.00	2.00	26.00	1.181	0.079	1.024	1.40		SEAM	*	*	*	*	*	*	



STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
30.00	2.30	25.40	1.181	0.091	1.000	1.60		SEAM					*		
30.00	2.50	25.00	1.181	0.098	0.984	1.72		WELD	*		*		*		
30.00	2.50	25.00	1.181	0.098	0.984	1.72		SEAM	*	*	*	*	*	*	*
30.00	2.60	24.80	1.181	0.102	0.976	1.78		WELD	*		*		*		
30.00	2.60	24.80	1.181	0.102	0.976	1.78		SEAM	*	*	*		*	*	*
30.00	3.00	24.00	1.181	0.118	0.945	2.03		WELD	*				*	*	*
30.00	3.00	24.00	1.181	0.118	0.945	2.03		SEAM	*	*	*	*	*	*	*
30.00	3.50	23.00	1.181	0.138	0.906	2.32		SEAM	*		*		*		
30.00	4.00	22.00	1.181	0.157	0.866	2.60		SEAM			*	*	*	*	*
30.00	5.00	20.00	1.181	0.197	0.787	3.13		SEAM	*		*	*	*	*	*
31.00	4.00	23.00	1.220	0.157	0.906	2.70		SEAM	*						
31.80	0.91	29.98	1.252	0.036	1.180	0.70	1.1/40DX.OJb	SEAM	*		*	*			
3180	1.00	29.80	1.252	0.039	1.173	0.77	1.1/40DX.039	WELD		*					*
31.80	1.00	29.80	1.252	0.039	1.173	0.77	1.114 OD X .039	SEAM		*					*
31.80	1.22	29.36	1.252	0.048	1.156	0.93	1.114 OD X .048	SEAM	*		*	*			
31.80	1.25	29.30	1.252	0.049	1.154	0.96	1.114 OD X .049	WELD	*						
31.80	1.63	28.54	1.252	0.064	1.124	1.23	1.1/4 OD X .064	WELD	*			*			
31.80	1.63	28.54	1.252	0.064	1.124	1.23	1.1/4 OD X .064	SEAM	*		*	*			
31.80	2.03	27.74	1.252	0.080	1.092	1.51	1.114 OD X .080	SEAM	*			*			
3180	264	26.52	1.252	0.104	1.044	1.93	1.1/40DX.104	SEAM			*	*			
31.80	318	25.44	1.252	0.125	1.002	2.28	1.1/40DX.125	SEAM	*		*	*			
31.80	4.78	22.24	1.252	0.188	0.876	3.23	1.114 OD X .188	SEAM			*	*	*	*	*
31.80	635	19.10	1.252	0.250	0.752	4.05	1.1/40DX.250	SEAM			*	*	*	*	*
3200	100	30.00	1.260	0.039	1.181	0.78		WELD	*						
32.00	1.00	30.00	1.260	0.039	1.181	0.78		SEAM			*				
32.00	150	29.00	1.260	0.059	1.142	1.15		WELD	*			*			*
32.00	150	29.00	1.260	0.059	1.142	1.15		SEAM	*		*				
32.00	2.00	28.00	1.260	0.079	1.102	1.50		WELD	*		*	*	*	*	*
32.00	2.00	28.00	1.260	0.079	1.102	1.50		SEAM	*		*	*	*	*	*
32.00	250	27.00	1.260	0.098	1.063	1.85		SEAM	*		*	*	*	*	*
32.00	3.00	26.00	1.260	0.118	1.024	2.18		SEAM	*		*	*	*	*	*
32.00	3.20	25.60	1.260	0.126	1.008	2.31		SEAM			*		*		
32.00	3.50	25.00	1.260	0.138	0.984	2.50		SEAM			*		*		
32.00	4.00	24.00	1.260	0.157	0.945	2.80		SEAM	*		*		*		
32.00	6.00	20.00	1.260	0.236	0.787	4.22		HBAR	*	*	*	*	*	*	*
32.00	8.00	16.00	1.260	0.315	0.630	5.19		HBAR	*	*	*	*	*	*	*
32.00	10.00	12.00	1.260	0.394	0.472	5.95		HBAR	*						
33.00	1.50	30.00	1.299	0.059	1.181	1.18		WELD	*	*	*	*	*	*	*
33.00	1.50	30.00	1.299	0.059	1.181	1.18		SEAM	*	*	*	*	*	*	*
33.00	2.50	28.00	1.299	0.098	1.102	1.91		SEAM	*						
33.00	4.00	25.00	1.299	0.157	0.984	2.90		SEAM	*					*	
33.00	6.50	20.00	1.299	0.256	0.787	4.65		HBAR	*						
33.40	1.65	30.10	1.315	0.065	1.185	1.31	1 SCH 5	SEAM	*	*	*	*	*	*	*
33.40	1.65	30.10	1.315	0.065	1.185	1.31	1 SCH 5	WELD		*	*	*	*	*	*
33.40	2.77	27.86	1.315	0.109	1.097	2.12	1 SCH 10	WELD	*	*	*	*	*	*	*
33.40	2.77	27.86	1.315	0.109	1.097	2.12	1 SCH 10	SEAM	*	*	*	*	*	*	*
33.40	3.38	26.64	1.315	0.133	1.049	2.54	1 SCH 40	SEAM	*	*	*	*	*	*	*
33.40	3.38	26.64	1.315	0.133	1.049	2.54	1 SCH 40	WELD		*	*	*	*	*	*
33.40	4.55	24.30	1.315	0.179	0.957	3.29	1 SCH 80	SEAM	*	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC		IMPERIAL			KGS/MTR		* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
33.40	6.35	20.70	1.315	0.250	0.815	4.30	1 SCH 160	SEAM	*	*	*	*	*	*	*
33.40	9.09	15.22	1.315	0.358	0.599	5.35	1 XXS	SEAM		*	*			*	
33.70	1.60	30.50	1.327	0.063	1.201	1.29		WELD	*	*	*	*	*	*	*
33.70	1.60	30.50	1.327	0.063	1.201	1.29		SEAM	*	*	*		*	*	
33.70	2.00	29.70	1.327	0.079	1.169	1.59		WELD	*	*	*	*	*	*	*
33.70	2.00	29.70	1.327	0.079	1.169	1.59		SEAM	*	*	*		*	*	
33.70	2.30	29.10	1.327	0.091	1.146	1.81		SEAM		*					
33.70	2.60	28.50	1.327	0.102	1.122	2.02		WELD	*		*		*		
33.70	2.60	28.50	1.327	0.102	1.122	2.02		SEAM	*	*	*		*	*	*
33.70	2.90	27.90	1.327	0.114	1.098	2.24		WELD	*		*		*		
33.70	2.90	27.90	1.327	0.114	1.098	2.24		SEAM			*		*		
33.70	3.20	27.30	1.327	0.126	1.075	2.44	1 ISO	WELD	*	*	*	*	*	*	*
33.70	3.20	27.30	1.327	0.126	1.075	2.44	1 ISO	SEAM	*	*	*	*	*	*	*
33.70	3.60	26.50	1.327	0.142	1.043	2.71		SEAM			*		*		
33.70	4.05	25.60	1.327	0.159	1.008	3.01		SEAM	*	*	*		*		
33.70	4.50	24.70	1.327	0.177	0.972	3.29		SEAM			*		*		
33.98	2.64	28.70	1.338	0.104	1.130	2.07	1 BSP LIGHT	SEAM		*	*	*		*	
33.98	3.65	26.68	1.338	0.144	1.050	2.77	1 BSP STANDARD	SEAM			*	*		*	
34.00	1.00	32.00	1.339	0.039	1.260	0.83		WELD	*				*		*
34.00	1.00	32.00	1.339	0.039	1.260	0.83		SEAM	*	*					
34.00	1.50	31.00	1.339	0.059	1.220	1.22		WELD	*	*			*		
34.00	1.50	31.00	1.339	0.059	1.220	1.22		SEAM	*	*			*		
34.00	2.00	30.00	1.339	0.079	1.181	1.60		WELD	*	*			*		
34.00	2.00	30.00	1.339	0.079	1.181	1.60		SEAM	*	*			*		
34.00	3.00	28.00	1.339	0.118	1.102	2.33		SEAM						*	
34.00	3.50	27.00	1.339	0.138	1.063	2.67		SEAM		*			*		
34.00	4.00	26.00	1.339	0.157	1.024	3.00		SEAM	*	*			*		
34.00	5.00	24.00	1.339	0.197	0.945	3.63		SEAM		*			*		
34.00	5.50	23.00	1.339	0.217	0.906	3.93		SEAM	*	*			*		
34.93	0.91	33.11	1.375	0.036	1.304	0.78	1.3/8 OD X .036	SEAM			*	*			
34.93	1.22	32.49	1.375	0.048	1.279	1.03	1.3/8 OD X .048	SEAM		*	*				
34.93	1.63	31.67	1.375	0.064	1.247	1.36	1.3/8 OD X .064	SEAM		*	*				
34.93	2.03	30.87	1.375	0.080	1.215	1.67	1.3/8 OD X .080	SEAM		*	*				
34.93	3.18	28.57	1.375	0.125	1.125	2.53	1.3/8 OD X .125	SEAM		*	*				
34.93	4.78	25.37	1.375	0.188	0.999	3.61	1.3/8 OD X .188	SEAM		*	*				
34.93	6.35	22.23	1.375	0.250	0.875	4.54	1.3/8 OD X .250	SEAM		*	*				
35.00	1.00	33.00	1.378	0.039	1.299	0.85		WELD	*				*		*
35.00	1.50	32.00	1.378	0.059	1.260	1.26		WELD	*	*	*	*	*		*
35.00	1.50	32.00	1.378	0.059	1.260	1.26		SEAM	*	*	*	*	*	*	
35.00	2.00	31.00	1.378	0.079	1.220	1.65		WELD	*		*	*	*		*
35.00	2.00	31.00	1.378	0.079	1.220	1.65		SEAM	*	*	*	*	*	*	
35.00	2.50	30.00	1.378	0.098	1.181	2.03		WELD	*	*	*	*	*		*
35.00	2.50	30.00	1.378	0.098	1.181	2.03		SEAM	*	*	*	*	*		*
35.00	3.00	29.00	1.378	0.118	1.142	2.40		SEAM		*	*	*	*	*	
35.00	4.00	27.00	1.378	0.157	1.063	3.10		SEAM	*						
35.00	5.00	25.00	1.378	0.197	0.984	3.76		SEAM		*	*	*	*	*	
36.00	1.00	34.00	1.417	0.039	1.339	0.88		SEAM					*		
36.00	2.00	32.00	1.417	0.079	1.260	1.70		WELD	*	*			*		

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
36.00	2.00	32.00	1.417	0.079	1.260	1.70		SEAM	*		*		*		
36.00	3.00	30.00	1.417	0.118	1.181	2.48		SEAM	*		*	*	*	*	
36.00	5.50	25.00	1.417	0.217	0.984	4.54		HBAR	*	*	*	*	*	*	*
36.00	8.00	20.00	1.417	0.315	0.787	6.06		HBAR	*	*	*	*	*	*	*
36.00	10.00	16.00	1.417	0.394	0.630	7.03		HBAR	*	*	*	*	*	*	*
<hr/>															
38.00	1.00	36.00	1.496	0.039	1.417	0.93		WELD	*	*	*		*	*	*
38.00	1.00	36.00	1.496	0.039	1.417	0.93		SEAM	*	*	*	*	*	*	*
38.00	1.50	35.00	1.496	0.059	1.378	1.37		WELD	*	*	*	*	*	*	*
38.00	1.50	35.00	1.496	0.059	1.378	1.37		SEAM	*	*	*	*	*	*	*
38.00	2.00	34.00	1.496	0.079	1.339	1.80		WELD	*	*	*	*	*	*	*
38.00	2.00	34.00	1.496	0.079	1.339	1.80		SEAM	*	*	*	*	*	*	*
38.00	2.50	33.00	1.496	0.098	1.299	2.22		SEAM	*	*	*	*	*	*	*
38.00	2.60	32.80	1.496	0.102	1.291	2.30		WELD	*	*	*	*	*	*	*
38.00	2.60	32.80	1.496	0.102	1.291	2.30		SEAM	*	*	*	*	*	*	*
38.00	3.00	32.00	1.496	0.118	1.260	2.63		SEAM	*	*	*	*	*	*	*
3800	3.60	30.80	1.496	0.142	1.213	3.10		SEAM	*	*	*	*	*	*	*
38.00	4.00	30.00	1.496	0.157	1.181	3.41		SEAM	*	*	*	*	*	*	*
38.00	4.50	29.00	1.496	0.177	1.142	3.77		SEAM	*	*	*	*	*	*	*
38.00	5.00	28.00	1.496	0.197	1.102	4.13		SEAM	*	*	*	*	*	*	*
38.00	6.00	26.00	1.496	0.236	1.024	4.81		SEAM	*	*	*	*	*	*	*
<hr/>															
3810	0.91	36.28	1.500	0.036	1.428	0.85	1.1/2	OD X .036	WELD		*		*		
3810	0.91	36.28	1.500	0.036	1.428	0.85	1.1/2	OD X .036	SEAM		*	*	*	*	
38.10	1.22	35.66	1.500	0.048	1.404	1.13	1 1/2	OD X .048	WELD	*		*			
38.10	1.22	35.66	1.500	0.048	1.404	1.13	1.1/2	OD X .048	SEAM	*	*	*	*	*	
3810	1.50	35.10	1.500	0.059	1.382	1.37	1.1/2	OD X .059	WELD	*		*			*
38.10	1.63	34.84	1.500	0.064	1.372	1.49	1.1/2	OD X .064	WELD	*		*			
38.10	1.63	34.84	1.500	0.064	1.372	1.49	1.1/2	OD X .064	SEAM	*	*	*	*	*	
3810	2.03	34.04	1.500	0.080	1.340	1.83	1.1/2	OD X .080	WELD	*		*			
38.10	2.03	34.04	1.500	0.080	1.340	1.83	1 1/2	OD X .080	SEAM	*	*	*	*	*	
38.10	2.64	32.82	1.500	0.104	1.292	2.34	1 1/2	OD X .104	SEAM	*	*	*	*	*	
38.10	3.18	31.74	1.500	0.125	1.250	2.78	1.1/2	OD X .125	SEAM	*	*	*	*	*	
38.10	4.78	28.54	1.500	0.188	1.124	3.99	1 1/2	OD X .188	SEAM	*	*	*	*	*	
3810	6.35	25.40	1.500	0.250	1.000	5.05	1.1/2	OD X .250	SEAM	*	*	*	*	*	
3810	7.95	22.20	1.500	0.313	0.874	6.00	1.1/2	OD X .313	SEAM	*	*	*	*	*	
<hr/>															
3950	4.60	30.30	1.555	0.181	1.193	4.02		SEAM			*		*		
<hr/>															
4000	1.00	38.00	1.575	0.039	1.496	0.98		WELD	*		*		*		
40.00	1.00	38.00	1.575	0.039	1.496	0.98		SEAM	*		*		*		
40.00	1.50	37.00	1.575	0.059	1.457	1.45		WELD	*		*	*	*	*	
40.00	1.50	37.00	1.575	0.059	1.457	1.45		SEAM	*		*	*	*	*	
40.00	2.00	36.00	1.575	0.079	1.417	1.90		WELD	*		*	*	*	*	*
40.00	2.00	36.00	1.575	0.079	1.417	1.90		SEAM	*	*	*	*	*	*	*
40.00	2.50	35.00	1.575	0.098	1.378	2.35		SEAM	*		*	*	*	*	
40.00	3.00	34.00	1.575	0.118	1.339	2.78		WELD	*		*	*	*	*	
40.00	3.00	34.00	1.575	0.118	1.339	2.78		SEAM	*		*	*	*	*	
40.00	4.00	32.00	1.575	0.157	1.260	3.61		SEAM	*		*	*	*	*	
40.00	5.00	30.00	1.575	0.197	1.181	4.38		SEAM	*	*	*	*	*	*	*
40.00	6.00	28.00	1.575	0.236	1.102	5.52		HBAR	*	*	*	*	*	*	*
40.00	7.50	25.00	1.575	0.295	0.984	6.59		HBAR	*	*	*	*	*	*	*
40.00	8.75	22.50	1.575	0.344	0.886	7.40		HBAR	*	*	*	*	*	*	*
40.00	10.00	20.00	1.575	0.394	0.787	8.11		HBAR	*	*	*	*	*	*	*



TELEPHONE: 01207 590055

FAX 01207 590059

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310	
METRIC			IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 2/3 WEEKS)									
MM	MM	MM	INCH	INCH	INCH											
41.00	1.00	39.00	1.614	0.039	1.535	1.00		SEAM					*			
41.00	4.00	33.00	1.614	0.157	1.299	3.71		SEAM					*			
41.28	1.63	38.02	1.625	0.064	1.497	1.62	1.5/8 OD X .064	SEAM	*		*	*				
41.28	2.03	37.22	1.625	0.080	1.465	2.00	1.5/8 OD X .080	SEAM	*		*	*				
41.28	3.18	34.92	1.625	0.125	1.375	3.03	1.5/8ODX.125	SEAM			*	*				
41.28	6.35	28.58	1.625	0.250	1.125	5.55	1.5/8 OD X .250	SEAM			*	*				
42.00	2.00	38.00	1.654	0.079	1.496	2.00		WELD	*						*	
42.00	2.00	38.00	1.654	0.079	1.496	2.00		SEAM	*		*	*	*			
42.00	3.00	36.00	1.654	0.118	1.417	2.93		SEAM			*	*	*			
42.00	5.00	32.00	1.654	0.197	1.260	4.63		SEAM			*	*	*			
42.00	6.00	30.00	1.654	0.236	1.181	5.41		SEAM	*		*	*	*			
42.16	1.65	38.86	1.660	0.065	1.530	1.67	1.1/4 SCH 5	SEAM	*	*	*	*	*	*	*	
42.16	1.65	38.86	1.660	0.065	1.530	1.67	1.1/4 SCH 5	WELD		*				*	*	
42.16	2.11	37.94	1.660	0.083	1.494	2.12		SEAM						*	*	
42.16	2.77	36.62	1.660	0.109	1.442	2.73	1.1/4SCH 10	SEAM	*	*	*	*	*	*	*	
42.16	2.77	36.62	1.660	0.109	1.442	2.73	1.1/4 SCH 10	WELD		*	*	*	*	*	*	
42.16	3.56	35.04	1.660	0.140	1.380	3.44	1.1/4 SCH 40	SEAM	*	*	*	*	*	*	*	
42.16	3.56	35.04	1.660	0.140	1.380	3.44	1.1/4 SCH 40	WELD		*				*	*	
42.16	4.85	32.46	1.660	0.191	1.278	4.53	1.1/4 SCH 80	SEAM	*	*	*	*	*	*	*	
42.16	6.35	29.46	1.660	0.250	1.160	5.69	1.1/4 SCH 160	SEAM	*	*	*	*	*	*	*	
42.40	1.60	39.20	1.669	0.063	1.543	1.63		WELD	*	*	*	*	*	*	*	
42.40	1.60	39.20	1.669	0.063	1.543	1.63		SEAM	*	*	*	*	*	*	*	
42.40	2.00	38.40	1.669	0.079	1.512	2.02		WELD	*	*	*	*	*	*	*	
42.40	2.00	38.40	1.669	0.079	1.512	2.02		SEAM	*	*	*	*	*	*	*	
42.40	2.60	37.20	1.669	0.102	1.465	2.59		WELD	*		*	*	*	*	*	
42.40	2.60	37.20	1.669	0.102	1.465	2.59		SEAM	*	*	*	*	*	*	*	
42.40	2.90	36.60	1.669	0.114	1.441	2.87		WELD	*							
42.40	3.20	36.00	1.669	0.126	1.417	3.14	1.1/4ISO	WELD	*	*	*	*	*	*	*	
42.40	3.20	36.00	1.669	0.126	1.417	3.14	1.1/4ISO	SEAM	*	*	*	*	*	*	*	
42.40	3.60	35.20	1.669	0.142	1.386	3.50		SEAM			*	*	*	*	*	
42.40	4.05	34.30	1.669	0.159	1.350	3.89		SEAM	*		*	*	*	*	*	
42.40	6.30	29.80	1.669	0.248	1.177	5.69		SEAM		*		*	*	*	*	
42.50	11.25	20.00	1.673	0.443	0.787	9.56		HBAR	*							
43.00	1.50	40.00	1.693	0.059	1.575	1.56		WELD	*	*	*	*	*	*	*	
43.00	1.50	40.00	1.693	0.059	1.575	1.56		SEAM	*	*			*	*	*	
43.00	5.50	32.00	1.693	0.217	1.260	5.16		SEAM			*	*	*	*	*	
43.00	6.75	29.50	1.693	0.266	1.161	6.62		HBAR			*	*	*	*	*	
44.00	2.00	40.00	1.732	0.079	1.575	2.10		SEAM	*			*	*	*	*	
44.00	3.00	38.00	1.732	0.118	1.496	3.08		SEAM	*			*	*	*	*	
44.50	1.22	42.06	1.752	0.048	1.656	1.32	1.3/4 OD X .048	SEAM			*	*	*	*	*	
44.50	1.50	41.50	1.752	0.059	1.634	1.62	1.3/4 OD X .059	WELD	*				*	*	*	
44.50	1.63	41.24	1.752	0.064	1.624	1.75	1.3/4 OD X .064	SEAM	*		*	*	*	*	*	
44.50	2.00	40.50	1.752	0.079	1.594	2.13	1.3/4 OD X .079	WELD	*		*	*	*	*	*	
44.50	2.00	40.50	1.752	0.079	1.594	2.13	1.3/4 OD X .079	SEAM	*	*	*	*	*	*	*	
44.50	2.50	39.50	1.752	0.098	1.555	2.63	1.3/4 OD X .098	SEAM	*		*	*	*	*	*	

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	310	
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
44.50	2.50	39.50	1.752	0.098	1.555	2.63	1.3/4 OD X .098	WELD						*	
44.50	2.60	39.30	1.752	0.102	1.547	2.73	1.3/4 OD X .102	WELD	*		*			*	
44.50	2.60	39.30	1.752	0.102	1.547	2.73	1.3/4 OD X .102	SEAM	*	*	*		*	*	
44.50	2.90	38.70	1.752	0.114	1.524	3.02	1.3/4 OD X .114	WELD	*		*		*		
44.50	2.90	38.70	1.752	0.114	1.524	3.02	1.3/40DX.114	SEAM	*	*	*	*	*	*	
44.50	3.00	38.50	1.752	0.118	1.516	3.12	1.3/40DX.118	SEAM			*				
44.50	3.18	38.14	1.752	0.125	1.502	3.29	1.3/4 OD X .125	SEAM	*		*	*	*	*	
44.50	4.00	36.50	1.752	0.157	1.437	4.06	1.3/40DX.157	SEAM	*		*	*	*		
44.50	4.78	34.94	1.752	0.188	1.376	4.75	1.3/4 OD X .188	SEAM			*	*			
44.50	5.50	33.50	1.752	0.217	1.319	5.37	1.3/4 OD X .220	SEAM	*						
44.50	6.35	31.80	1.752	0.250	1.252	6.07	1.3/4 OD X .250	SEAM	*			*			
44.50	9.53	25.44	1.752	0.375	1.002	8.34	1.3/4 OD X .375	SEAM			*	*			
45.00	1.00	43.00	1.772	0.039	1.693	1.10		SEAM	*						
45.00	1.50	42.00	1.772	0.059	1.654	1.63		SEAM	*		*				
45.00	1.50	42.00	1.772	0.059	1.654	1.63		WELD			*				
45.00	2.00	41.00	1.772	0.079	1.614	2.15		SEAM	*			*			
45.00	2.00	41.00	1.772	0.079	1.614	2.15		WELD						*	
45.00	3.00	39.00	1.772	0.118	1.535	3.16		WELD	*						
45.00	3.50	38.00	1.772	0.138	1.496	3.64		SEAM			*		*		
45.00	5.00	35.00	1.772	0.197	1.378	5.41		HBAR	*			*			
45.00	5.00	35.00	1.772	0.197	1.378	5.01		SEAM			*				
45.00	6.50	32.00	1.772	0.256	1.260	6.77		HBAR	*	*	*	*	*	*	
45.00	6.50	32.00	1.772	0.256	1.260	6.27		SEAM				*			
45.00	7.50	30.00	1.772	0.295	1.181	7.60		HBAR			*	*			
45.00	8.50	28.00	1.772	0.335	1.102	8.39		HBAR	*	*	*	*	*	*	
45.00	10.00	25.00	1.772	0.394	0.984	9.46		HBAR	*						
45.00	11.25	22.50	1.772	0.443	0.886	10.27		HBAR	*						
45.00	12.50	20.00	1.772	0.492	0.787	10.98		HBAR	*	*	*	*	*	*	
47.63	4.78	38.07	1.875	0.188	1.499	5.13	1.7/8 OD X .188	SEAM			*	*			
48.00	1.50	45.00	1.890	0.059	1.772	1.75		WELD	*						
48.00	2.50	43.00	1.890	0.098	1.693	2.85		SEAM			*				
48.00	4.00	40.00	1.890	0.157	1.575	4.41		SEAM	*	*					
48.26	1.65	44.96	1.900	0.065	1.770	1.93	1 1/2 SCH 5	SEAM	*	*	*	*	*	*	
48.26	1.65	44.96	1.900	0.065	1.770	1.93	1.1/2 SCH 5	WELD		*	*			*	
48.26	2.77	42.72	1.900	0.109	1.682	3.16	1.1/2 SCH 10	SEAM	*	*	*	*	*	*	
48.26	2.77	42.72	1.900	0.109	1.682	3.16	1.1/2 SCH 10	WELD		*	*			*	
48.26	3.68	40.90	1.900	0.145	1.610	4.11	1.1/2 SCH 40	SEAM	*	*	*	*	*	*	
48.26	3.68	40.90	1.900	0.145	1.610	4.11	1.1/2 SCH 40	WELD		*	*			*	
48.26	4.47	39.32	1.900	0.176	1.548	4.90	1.1/2 BSP HEAVY	SEAM			*	*			
48.26	5.08	38.10	1.900	0.200	1.500	5.49	1.1/2 SCH 80	SEAM	*	*	*	*	*	*	
48.26	7.14	33.98	1.900	0.281	1.338	7.35	1.1/2 SCH 160	SEAM	*	*	*	*	*	*	
48.26	10.16	27.94	1.900	0.400	1.100	9.69	1.1/2 XXS	SEAM		*	*			*	
48.30	1.60	45.10	1.902	0.063	1.776	1.87		WELD	*	*	*	*	*	*	
48.30	1.60	45.10	1.902	0.063	1.776	1.87		SEAM	*	*	*	*	*	*	
48.30	2.00	44.30	1.902	0.079	1.744	2.32		WELD	*	*	*	*	*	*	
48.30	2.00	44.30	1.902	0.079	1.744	2.32		SEAM	*	*	*	*	*	*	
48.30	2.30	43.70	1.902	0.091	1.720	2.65		SEAM			*				
48.30	2.60	43.10	1.902	0.102	1.697	2.98		WELD	*		*	*	*	*	
48.30	2.60	43.10	1.902	0.102	1.697	2.98		SEAM	*	*	*	*	*	*	

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
4830	277	42.76	1902	0109	1.683	3.16		WELD		*					*
4830	290	42.50	1.902	0.114	1.673	3.30		WELD	*						
4830	290	42.50	1.902	0.114	1.673	3.30		SEAM			*		*		
4830	3.00	4230	1902	0.118	1.665	3.40		WELD	*						
48.30	320	41.90	1.902	0126	1.650	3.61	1.112 ISO	WELD	*	*	*	*	*	*	*
48.30	320	41.90	1.902	0126	1.650	3.61	1.112 ISO	SEAM	*	*	*	*	*	*	*
48.30	3.60	41.10	1.902	0142	1.618	4.03		WELD			*		*		
4830	3.60	41.10	1.902	0.142	1.618	4.03		SEAM			*		*		
4830	4.05	40.20	1.902	0159	1.583	4.49		SEAM	*		*		*		
4830	4.60	3910	1902	0.181	1.539	5.03		SEAM			*		*		
4830	500	3830	1902	0.197	1508	5.42		SEAM			*		*		
4830	650	3530	1902	0.256	1.390	6.80		SEAM			*		*		
4830	7.10	34.10	1902	0.280	1.343	7.32		SEAM					*		*
<hr/>															
48.41	3.25	41.91	1906	0128	1.650	3.68	1.112 ISO STANDARD	SEAM			*		*		
<hr/>															
49.00	5.50	38.00	1.929	0.217	1.496	5.99		SEAM			*		*		
<hr/>															
50.00	100	48.00	1969	0039	1.890	123		WELD	*						
5000	1.00	48.00	1.969	0039	1890	123		SEAM	*		*				
5000	150	47.00	1.969	0.059	1.850	1.82		WELD	*				*		
50.00	150	47.00	1.969	0059	1.850	1.82		SEAM	*		*		*		
5000	2.00	46.00	1.969	0.079	1.811	2.40		WELD	*		*		*		*
50.00	2.00	46.00	1.969	0.079	1.811	2.40		SEAM	*	*	*		*	*	*
5000	250	45.00	1.969	0098	1.772	2.97		SEAM	*				*		
5000	3.00	44.00	1.969	0.118	1732	3.53		SEAM	*		*		*	*	*
50.00	4.00	42.00	1.969	0.157	1.654	4.61		SEAM			*		*		*
5000	5.00	40.00	1.969	0.197	1.575	563		SEAM	*		*		*	*	*
5000	6.00	38.00	1.969	0.236	1,496	6.61		SEAM	*		*		*	*	*
50.00	7.00	36.00	1.969	0.276	1,417	8.14		HBAR	*	*	*		*	*	*
5000	9.00	32.00	1.969	0.354	1260	9.98		HBAR	*	*	*		*	*	*
50.00	12.50	25.00	1.969	0.492	0984	12.68		HBAR	*	*	*		*	*	*
<hr/>															
5080	0.91	48.98	2.000	0036	1928	1.14	2 OD X .036	SEAM					*		
50.80	1.22	48.36	2.000	0.048	1904	151	2 OD X .048	WELD	*				*		
50.80	1.22	48.36	2000	0048	1904	151	2 OD X .048	SEAM	*		*		*		
5080	150	4780	2000	0.059	1.882	185	2 OD X .059	WELD	*	*			*		*
50.80	1.63	47.54	2.000	0.064	1872	2.01	2 OD X .064	WELD	*				*		
50.80	1.63	4754	2.000	0064	1.872	2.01	2 OD X .064	SEAM	*		*		*		
50.80	2.03	46.74	2.000	0.080	1.840	2.48	2 OD X .080	WELD	*				*		
50.80	2.03	46.74	2.000	0.080	1.840	2.48	2 OD X .080	SEAM	*		*		*		
5080	250	45.80	2.000	0.098	1.803	3.02	2 OD X .098	WELD	*				*		
5080	264	45.52	2.000	0104	1.792	3.18	2 OD X .104	SEAM	*		*		*		
50.80	3.18	44.44	2.000	0.125	1.750	3.79	2 OD X125	SEAM	*		*		*		
50.80	4.78	41.24	2.000	0188	1.624	5.51	2 OD X .188	SEAM			*		*		
50.80	6.35	38.10	2.000	0.250	1.500	7.07	2 OD X .250	SEAM	*	*	*		*		*
50.80	9.53	31.74	2.000	0.375	1.250	9.85	2 OD X .375	SEAM			*		*		
50.80	12.70	25.40	2.000	0.500	1.000	12.12	2 OD X .500	SEAM			*		*		
<hr/>															
51.00	1.00	4900	2.008	0.039	1.929	1.25		SEAM	*		*		*		
51.00	1.50	48.00	2.008	0.059	1.890	1.86		WELD	*		*		*	*	
51.00	1.60	47.80	2.008	0.063	1.882	1.98		WELD		*			*		*
51.00	2.00	47.00	2.008	0.079	1.850	2.45		WELD	*		*		*	*	
51.00	2.00	47.00	2.008	0.079	1.850	2.45		SEAM	*				*	*	

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316316TI316L	310	
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)					
MM	MM	MM	INCH	INCH	INCH									
51.00	2.60	45.80	2.008	0.102	1.803	3.15		WELD	*		*	*		
51.00	2.60	45.80	2.008	0.102	1.803	3.15		SEAM	*	*	*	*	*	
51.00	2.90	45.20	2.008	0.114	1.780	3.49		SEAM			*	*		
51.00	4.00	43.00	2.008	0.157	1.693	4.71		SEAM			*	*		
52.00	1.00	50.00	2.047	0.039	1.969	1.28		WELD	*			*		
52.00	1.00	50.00	2.047	0.039	1.969	1.28		SEAM	*			*		
52.00	1.50	49.00	2.047	0.059	1.929	1.90		WELD	*		*	*		
52.00	1.50	49.00	2.047	0.059	1.929	1.90		SEAM	*		*	*		
52.00	2.00	48.00	2.047	0.079	1.890	2.50		WELD	*		*	*		
52.00	2.00	48.00	2.047	0.079	1.890	2.50		SEAM	*		*	*	*	
52.00	4.00	44.00	2.047	0.157	1.732	4.81		SEAM			*	*		
53.00	1.50	50.00	2.087	0.059	1.969	1.93		WELD	*	*	*	*	*	
53.00	1.50	50.00	2.087	0.059	1.969	1.93		SEAM	*	*	*	*	*	
53.00	3.00	47.00	2.087	0.118	1.850	3.76		SEAM	*					
53.00	4.00	45.00	2.087	0.157	1.772	4.91		SEAM			*	*		
53.00	4.50	44.00	2.087	0.177	1.732	5.46		SEAM			*	*		
54.00	1.50	51.00	2.126	0.059	2.008	1.97	2.1/8 OD X .059	WELD	*			*		
54.00	1.63	50.74	2.126	0.064	1.998	2.14	2.1/8 OD X .064	WELD	*	*			*	
54.00	1.63	50.74	2.126	0.064	1.998	2.14	2.1/8 OD X .064	SEAM	*	*	*	*	*	
54.00	2.00	50.00	2.126	0.079	1.969	2.60	2.1/8 OD X .079	WELD	*	*	*	*	*	
54.00	2.00	50.00	2.126	0.079	1.969	2.60	2.1/8 OD X .079	SEAM	*	*	*	*	*	
54.00	2.50	49.00	2.126	0.098	1.929	3.22	2.1/8 OD X .098	SEAM			*	*		
54.00	3.00	48.00	2.126	0.118	1.890	3.83	2.1/8 OD X .118	SEAM	*		*	*		
54.00	3.18	47.64	2.126	0.125	1.876	4.05	2.1/8 OD X .125	SEAM			*	*		
54.00	4.78	44.44	2.126	0.188	1.750	5.89	2.1/8 OD X .188	SEAM			*	*		
5450	4.70	45.10	2.146	0.185	1.776	5.86		SEAM			*	*		
55.00	2.00	51.00	2.165	0.079	2.008	2.65		SEAM		*				
55.00	2.50	50.00	2.165	0.098	1.969	3.29		SEAM	*				*	
55.00	5.00	45.00	2.165	0.197	1.772	6.26		SEAM	*			*	*	
56.00	5.50	45.00	2.205	0.217	1.772	7.51		HBAR			*	*		
56.00	8.00	40.00	2.205	0.315	1.575	10.39		HBAR	*	*	*	*	*	
56.00	10.00	36.00	2.205	0.394	1.417	12.44		HBAR	*	*	*	*	*	
56.00	14.00	28.00	2.205	0.551	1.102	15.90		HBAR	*	*	*	*	*	
57.00	1.50	54.00	2.244	0.059	2.126	2.08		WELD	*		*	*	*	
57.00	2.00	53.00	2.244	0.079	2.087	2.75		WELD	*		*	*	*	
57.00	2.00	53.00	2.244	0.079	2.087	2.75		SEAM	*		*	*	*	
57.00	2.30	52.40	2.244	0.091	2.063	3.15		SEAM			*	*		
57.00	2.50	52.00	2.244	0.098	2.047	3.41		WELD	*		*	*	*	
57.00	2.50	52.00	2.244	0.098	2.047	3.41		SEAM		*	*	*	*	
57.00	2.60	51.80	2.244	0.102	2.039	3.54		SEAM	*		*	*	*	
57.00	2.60	51.80	2.244	0.102	2.039	3.54		WELD			*	*	*	
57.00	2.90	51.20	2.244	0.114	2.016	3.93		SEAM	*	*	*	*	*	
57.00	2.90	51.20	2.244	0.114	2.016	3.93		WELD			*	*	*	
57.00	3.00	51.00	2.244	0.118	2.008	4.06		WELD	*		*	*	*	
57.00	3.50	50.00	2.244	0.138	1.969	4.69		SEAM			*	*	*	
57.00	4.00	49.00	2.244	0.157	1.929	5.31		SEAM	*		*	*	*	
57.00	4.50	48.00	2.244	0.177	1.890	5.92		SEAM			*	*	*	

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310	
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
57.00	5.00	47.00	2.244	0.197	1.850	6.51		SEAM			•	•	•		
57.00	6.30	44.40	2.244	0.248	1.748	8.00		SEAM			•				
57.00	6.50	44.00	2.244	0.256	1.732	8.22		SEAM			•	•	•		
57.00	15.50	26.00	2.244	0.610	1.024	17.40		HBAR	•						
<hr/>															
57.15	1.63	53.89	2.250	0.064	2.122	2.27	2.1/4 OD X .064	SEAM	*		*	*			
57.15	3.18	50.79	2.250	0.125	2.000	4.30	2.1/4ODX.125	SEAM	*		*	*			
57.15	4.78	47.59	2.250	0.188	1.874	6.27	2.1/4 OD X .188	SEAM	*		•	*			
57.15	6.35	44.45	2.250	0.250	1.750	8.08	2.1/4 OD X .250	SEAM	*		*	*			
57.15	9.53	38.09	2.250	0.375	1.500	11.36	2.1/4 OD X .375	SEAM			*	*			
<hr/>															
58.00	2.60	52.80	2.283	0.102	2.079	3.61		SEAM			*				
58.00	13.00	32.00	2.283	0.512	1.260	15.82		HBAR	•						
<hr/>															
59.00	11.75	35.50	2.323	0.463	1.398	15.01		HBAR	*						
<hr/>															
60.00	1.00	58.00	2.362	0.039	2.283	1.48		SEAM			*				
60.00	2.00	56.00	2.362	0.079	2.205	2.90		WELD	*						
60.00	3.00	54.00	2.362	0.118	2.126	4.28		WELD	*						
60.00	5.00	50.00	2.362	0.197	1.969	6.89		SEAM	*	*	*		*	•	
60.00	6.00	48.00	2.362	0.236	1.890	8.11		SEAM		*					
60.00	10.00	40.00	2.362	0.394	1.575	13.52		HBAR	*		*	*			
<hr/>															
60.30	1.65	57.00	2.374	0.065	2.244	2.42	2 SCH 5	WELD	*	•	•	*	*	*	
60.30	1.65	57.00	2.374	0.065	2.244	2.42	2 SCH 5	SEAM	*	•	*	*	•	*	
60.30	2.00	56.30	2.374	0.079	2.217	2.92	2.3/8 OD X .079	WELD	*	•	•	*	•	*	
60.30	2.00	56.30	2.374	0.079	2.217	2.92	2.3/8 OD X .079	SEAM	*	•	•	•	*	*	
60.30	2.11	56.08	2.374	0.083	2.208	3.07	2.3/8 OD X .083	WELD						•	
60.30	2.30	55.70	2.374	0.091	2.193	3.34	2.3/8 OD X .091	SEAM			•		*		
60.30	2.60	55.10	2.374	0.102	2.169	3.76	2.3/8 OD X .102	WELD	*		•	*	*		
60.30	2.60	55.10	2.374	0.102	2.169	3.76	2.3/8 OD X .102	SEAM	*	•	*	*	*	•	
60.30	2.77	54.76	2.374	0.109	2.156	3.99	2 SCH 10	SEAM	*	*	•	•	•	*	
60.30	2.77	54.76	2.374	0.109	2.156	3.99	2 SCH 10	WELD		*	•		*	*	
60.30	2.90	54.50	2.374	0.114	2.146	4.17	2.3/8 OD X.114	WELD	*		*	*	*	*	
60.30	2.90	54.50	2.374	0.114	2.146	4.17	2.3/8 OD X .114	SEAM	*		*	*	*	*	
60.30	3.00	54.30	2.374	0.118	2.138	4.30	2.3/8 OD X .118	WELD			*	*	*	*	
60.30	3.20	53.90	2.374	0.126	2.122	4.58	2.3/8 OD X .126	WELD	*		*	*	*	*	
60.30	3.20	53.90	2.374	0.126	2.122	4.58	2.3/8 OD X .126	SEAM	*		*	*	*	*	
60.30	3.60	53.10	2.374	0.142	2.091	5.11	21S0	WELD	*	*	*	•	*	*	
60.30	3.60	53.10	2.374	0.142	2.091	5.11	21S0	SEAM	*	•	*	*	*	*	
60.30	3.91	52.48	2.374	0.154	2.066	5.52	2 SCH 40	WELD	*	•	*	*	*	*	
60.30	3.91	52.48	2.374	0.154	2.066	5.52	2 SCH 40	SEAM	*	*	*	*	*	*	
60.30	4.00	52.30	2.374	0.157	2.059	5.64	2.3/8 OD X .157	SEAM			*	*	*	*	
60.30	4.50	51.30	2.374	0.177	2.020	6.29	2.3/8 OD X .177	SEAM	*		*	*	*	*	
60.30	4.78	50.74	2.374	0.188	1.998	6.65	2.3/8 OD X .188	SEAM			*	*	*	*	
60.30	5.00	50.30	2.374	0.197	1.980	6.92	2.3/8 OD X .197	SEAM			*	*	*	*	
60.30	5.54	49.22	2.374	0.218	1.938	7.60	2 SCH 80	SEAM	*	*	•	*	*	•	
60.30	6.35	47.60	2.374	0.250	1.874	8.58	2.3/8 OD X .250	SEAM				•			
60.30	7.10	46.10	2.374	0.280	1.815	9.46	2.3/8 OD X .280	SEAM					*		
60.30	7.62	45.06	2.374	0.300	1.774	10.05	2.3/8 OD X .300	SEAM				•			
60.30	8.00	44.30	2.374	0.315	1.744	10.48	2.3/8 OD X .315	SEAM			*	*	*	*	
60.30	8.74	42.82	2.374	0.344	1.686	11.28	2 SCH 160	SEAM	•	*	*	*	•	*	
60.30	10.00	40.30	2.374	0.394	1.587	12.60	2.3/8 OD X .394	SEAM				*	*	*	
60.30	11.07	38.16	2.374	0.436	1.502	13.65	2 XXS	SEAM		*	*		*	*	

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310	
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
63.00	1.50	60.00	2.480	0.059	2.362	2.31		WELD		*				*	
63.00	3.50	56.00	2.480	0.138	2.205	5.21		SEAM	*						
63.00	6.50	50.00	2.480	0.256	1.969	9.94		HBAR	*	*	*	*		*	
63.00	9.00	45.00	2.480	0.354	1.772	13.14		HBAR	*	*	*	*		*	
63.00	11.50	40.00	2.480	0.453	1.575	16.02		HBAR	*	*	*	*		*	
63.00	13.50	36.00	2.480	0.531	1.417	18.07		HBAR	*	*	*	*		*	
63.00	15.50	32.00	2.480	0.610	1.260	19.92		HBAR	*	*	*	*		*	
63.50	1.50	60.50	2.500	0.059	2.382	2.33	2.1/2 OD X .059	WELD	*		*				
63.50	1.63	60.24	2.500	0.064	2.372	2.53	2.1/2 OD X .064	WELD	*	*		*		*	
63.50	1.63	60.24	2.500	0.064	2.372	2.53	2.1/2 OD X .064	SEAM	*		*	*	*		
63.50	2.03	59.44	2.500	0.080	2.340	3.12	2.1/2 OD X .080	WELD	*						
63.50	2.03	59.44	2.500	0.080	2.340	3.12	2.1/2 OD X .080	SEAM			*	*			
63.50	2.60	58.30	2.500	0.102	2.295	3.96	2.1/2 OD X .102	WELD	*						
63.50	2.60	58.30	2.500	0.102	2.295	3.96	2.1/2 OD X .102	SEAM	*	*	*	*	*	*	
63.50	3.18	57.14	2.500	0.125	2.250	4.80	2.1/2 OD X .125	SEAM	*		*	*			
63.50	3.50	56.50	2.500	0.138	2.224	5.26	2.1/2 OD X .138	SEAM			*				
63.50	4.78	53.94	2.500	0.188	2.124	7.03	2.1/2 OD X .188	SEAM	*		*				
63.50	6.35	50.80	2.500	0.250	2.000	9.09	2.1/2 OD X .250	SEAM	*	*	*	*		*	
63.50	7.10	49.30	2.500	0.280	1.941	10.03	2.1/2 OD X .280	SEAM			*				
63.50	7.95	47.60	2.500	0.313	1.874	11.06	2.1/2 OD X .313	SEAM			*				
63.50	9.53	44.44	2.500	0.375	1.750	12.88	2.1/2 OD X .375	SEAM				*			
63.50	12.70	38.10	2.500	0.500	1.500	16.15	2.1/2 OD X .500	SEAM			*				
63.50	19.05	25.40	2.500	0.750	1.000	22.90	2.1/2 OD X .750	HBAR	*						
64.00	2.00	60.00	2.520	0.079	2.362	3.10		WELD	*	*			*	*	
6400	2.00	60.00	2.520	0.079	2.362	3.10		SEAM	*				*	*	
65.00	2.50	60.00	2.559	0.098	2.362	3.91		SEAM	*		*			*	
65.00	3.00	59.00	2.559	0.118	2.323	4.66		SEAM			*		*		
65.00	3.50	58.00	2.559	0.138	2.283	5.39		SEAM	*		*		*		
65.50	8.50	48.50	2.579	0.335	1.909	13.10		HBAR	*						
66.00	10.50	45.00	2.598	0.413	1.772	15.76		HBAR	*						
66.30	4.80	56.70	2.610	0.189	2.232	7.39		SEAM			*		*		
6668	1.63	63.42	2.625	0.064	2.497	2.66	2.5/8 OD X .064	SEAM			*	*			
66.68	12.70	41.28	2.625	0.500	1.625	17.17	2.5/8 OD X .064	SEAM			*				
68.00	1.50	65.00	2.677	0.059	2.559	2.50		WELD	*		*	*	*		
68.00	2.50	63.00	2.677	0.098	2.480	4.10		SEAM			*				
68.00	2.60	62.80	2.677	0.102	2.472	4.26		SEAM	*						
68.00	4.00	60.00	2.677	0.157	2.362	6.41		SEAM	*						
68.50	1000	48.50	2.697	0.394	1.909	15.82		HBAR	*						
69.00	2.00	65.00	2.717	0.079	2.559	3.36		WELD	*	*	*	*	*	*	
69.85	1.63	66.59	2.750	0.064	2.622	2.78	2.3/4 OD X .064	SEAM	*		*	*			
69.85	2.39	65.07	2.750	0.094	2.562	4.04	2.3/4 OD X .094	SEAM			*	*			
69.85	3.18	63.49	2.750	0.125	2.500	5.31	2.3/4 OD X .125	SEAM	*		*	*			



TELEPHONE: 01207 590055

FAX 01207 590059

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
69.85	4.78	60.29	2.750	0.188	2.374	7.79	2.3/4 OD X .188	SEAM			*	*			
69.85	6.35	57.15	2.750	0.250	2.250	10.10	2.3/4 OD X .250	SEAM			*	*			
69.85	9.53	50.79	2.750	0.375	2.000	14.39	2.3/4 OD X .375	SEAM			*	*			
70.00	1.50	67.00	2.756	0.059	2.638	2.57		WELD	*						
70.00	2.00	66.00	2.756	0.079	2.598	3.41		WELD	*	*	*	*	*	*	
70.00	2.00	66.00	2.756	0.079	2.598	3.41		SEAM	*	*	*	*	*	*	
70.00	2.50	65.00	2.756	0.098	2.559	4.23		SEAM	*	*	*	*	*	*	
70.00	2.90	64.20	2.756	0.114	2.528	4.87		WELD	*				*	*	
70.00	2.90	64.20	2.756	0.114	2.528	4.87		SEAM	*	*	*	*	*	*	*
70.00	3.00	64.00	2.756	0.118	2.520	5.03		WELD	*			*			
70.00	3.00	64.00	2.756	0.118	2.520	5.03		SEAM	*	*	*	*	*	*	
70.00	4.00	62.00	2.756	0.157	2.441	6.61		SEAM	*	*	*	*	*	*	
70.00	4.50	61.00	2.756	0.177	2.402	7.38		SEAM		*	*	*	*	*	*
70.00	5.00	60.00	2.756	0.197	2.362	8.14		SEAM		*	*	*	*	*	
70.00	7.00	56.00	2.756	0.276	2.205	11.04		SEAM	*	*	*	*	*	*	
70.00	10.00	50.00	2.756	0.394	1.969	16.22		HBAR	*	*	*	*	*	*	
70.00	12.50	45.00	2.756	0.492	1.172	18.00		SEAM				*			
71.00	7.50	56.00	2.795	0.295	2.205	12.88		HBAR	*	*	*	*	*	*	*
71.00	9.00	53.00	2.795	0.354	2.087	15.09		HBAR	*	*	*	*	*	*	*
71.00	13.00	45.00	2.795	0.512	1.772	20.39		HBAR	*	*	*	*	*	*	*
71.00	15.50	40.00	2.795	0.610	1.575	23.26		HBAR	*	*	*	*	*	*	*
71.00	17.50	36.00	2.795	0.689	1.417	25.32		HBAR	*	*	*	*	*	*	*
73.00	1.50	70.00	2.874	0.059	2.756	2.69		WELD	*	*					*
73.00	2.50	68.00	2.874	0.098	2.677	4.41		WELD							*
73.00	4.00	65.00	2.874	0.157	2.559	6.91		SEAM	*						
73.00	5.00	63.00	2.874	0.197	2.480	8.51		SEAM		*					
73.03	2.11	68.81	2.875	0.083	2.709	3.75	2.1/2 SCH 5	SEAM	*	*	*	*	*	*	*
73.03	2.11	68.81	2.875	0.083	2.709	3.75	2.1/2 SCH 5	WELD		*					*
73.03	3.05	66.93	2.875	0.120	2.635	5.34	2.1/2 SCH 10	SEAM	*	*	*	*	*	*	*
73.03	3.05	66.93	2.875	0.120	2.635	5.34	2.1/2 SCH 10	WELD		*					*
73.03	5.16	62.71	2.875	0.203	2.469	8.77	2.1/2 SCH 40	SEAM	*	*	*	*	*	*	*
73.03	7.01	59.01	2.875	0.276	2.323	11.59	2.1/2 SCH 80	SEAM	*	*	*	*	*	*	*
73.03	9.53	53.97	2.875	0.375	2.125	15.15	2.1/2 SCH 160	SEAM	*	*	*	*	*	*	*
74.00	2.00	70.00	2.913	0.079	2.756	3.61		WELD		*					*
74.00	4.00	66.00	2.913	0.157	2.598	7.01		SEAM	*				*		
75.00	2.50	70.00	2.953	0.098	2.756	4.54		SEAM	*						
75.00	5.00	65.00	2.953	0.197	2.559	8.76		SEAM			*				
75.00	7.50	60.00	2.953	0.295	2.362	13.69		HBAR	*	*	*	*	*	*	*
75.00	12.50	50.00	2.953	0.492	1.969	21.12		HBAR	*	*	*	*	*	*	*
75.00	17.50	40.00	2.953	0.689	1.575	27.22		HBAR	*	*	*	*	*	*	*
76.00	4.00	68.00	2.992	0.157	2.677	7.21		SEAM			*				
76.00	5.00	66.00	2.992	0.197	2.598	8.89		SEAM	*	*	*	*	*	*	*
76.00	5.50	65.00	2.992	0.217	2.559	9.71		SEAM			*		*	*	*
76.00	6.00	64.00	2.992	0.236	2.520	10.52		SEAM	*	*	*	*	*	*	*
76.00	8.00	60.00	2.992	0.315	2.362	14.71		HBAR		*	*	*	*	*	*
76.00	9.00	58.00	2.992	0.354	2.283	16.31		HBAR	*						
76.00	10.00	56.00	2.992	0.394	2.205	17.85		HBAR		*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
76.00	17.00	42.00	2.992	0.669	1.654	27.13		HBAR	*						
76.20	1.63	72.94	3.000	0.064	2.872	3.04	3 OD X .064	WELD	*	*	*	*	*	*	*
76.20	1.63	72.94	3.000	0.064	2.872	3.04	3 OD X .064	SEAM	*		*	*	*		
76.20	2.03	72.14	3.000	0.080	2.840	3.77	3 OD X .080	WELD	*	*	*	*	*	*	*
76.20	2.03	72.14	3.000	0.080	2.840	3.77	3 OD X .080	SEAM	*	*	*	*	*	*	*
76.20	2.30	71.60	3.000	0.091	2.819	4.26	3 OD X .091	WELD			*	*	*		
76.20	2.30	71.60	3.000	0.091	2.819	4.26	3 OD X .091	SEAM			*		*		
76.20	2.64	70.92	3.000	0.104	2.792	4.86	3 OD X .104	WELD	*	*	*		*		
76.20	2.64	70.92	3.000	0.104	2.792	4.86	30DX.104	SEAM	*		*	*	*	*	*
76.20	2.90	70.40	3.000	0.114	2.772	5.32	3 OD X .114	WELD	*		*	*	*	*	*
76.20	2.90	70.40	3.000	0.114	2.772	5.32	3 OD X .114	SEAM	*	*	*	*	*	*	*
76.20	3.18	69.84	3.000	0.125	2.750	5.81	3 OD X .125	WELD	*		*		*		
76.20	3.18	69.84	3.000	0.125	2.750	5.81	3 OD X .125	SEAM	*		*	*	*	*	*
76.20	3.60	69.00	3.000	0.142	2.717	6.54	2.112 ISO	WELD	*	*	*	*	*	*	*
76.20	3.60	69.00	3.000	0.142	2.717	6.54	2.112 ISO	SEAM	*	*	*	*	*	*	*
76.20	4.00	68.20	3.000	0.157	2.685	7.23	3 OD X .157	SEAM			*		*		
76.20	4.50	67.20	3000	0.177	2.646	8.08	3 OD X .177	SEAM	*	*	*	*	*	*	*
76.20	4.78	66.64	3.000	0.188	2.624	8.55	3 OD X .188	SEAM			*	*			
76.20	5.00	66.20	3.000	0.197	2.606	8.91	3 OD X .197	SEAM					*		
76.20	6.35	63.50	3.000	0.250	2.500	11.11	3 OD X .250	SEAM	*	*	*	*	*	*	*
76.20	7.10	62.00	3.000	0.280	2.441	12.28	3 OD X .280	SEAM			*				
76.20	9.53	57.14	3.000	0.375	2.250	15.91	3 OD X .375	SEAM	*		*	*			
76.20	12.70	50.80	3.000	0.500	2.000	20.19	3 OD X .500	SEAM			*				
78.00	1.50	75.00	3071	0.059	2.953	2.87		WELD	*			*			
79.00	2.00	75.00	3.110	0.079	2.953	3.86		WELD	*			*			
79.38	1.63	76.12	3.125	0.064	2.997	3.17	3.1/8 OD X .064	SEAM			*	*			
80.00	2.00	76.00	3.150	0.079	2.992	3.91		WELD	*						
80.00	2.00	76.00	3.150	0.079	2.992	3.91		SEAM	*		*		*	*	
80.00	2.50	75.00	3.150	0.098	2.953	4.85		SEAM	*						
80.00	3.00	74.00	3.150	0.118	2.913	5.78		WELD	*						
80.00	4.00	72.00	3.150	0.157	2.835	7.61		SEAM	*		*		*		
80.00	5.00	70.00	3.150	0.197	2.756	9.39		SEAM	*		*	*	*		
8000	8.50	63.00	3.150	0.335	2,480	16.44		HBAR	*	*	*	*	*	*	*
8000	15.00	50.00	3.150	0.591	1,969	26.36		HBAR	*	*	*	*	*	*	*
80.00	1750	45.00	3150	0.689	1.772	29.58		HBAR	*	*	*	*	*	*	*
8000	2000	40.00	3.150	0.787	1.575	32.45		HBAR	*	*	*	*	*	*	*
8000	22.00	36.00	3.150	0.866	1,417	34.51		HBAR			*				
82.00	4.90	72.20	3.228	0.193	2.843	9.46		SEAM			*		*		
82.55	1.63	79.29	3.250	0.064	3.122	3.30	3.1/4 OD X .064	SEAM			*				
82.55	3.18	76.19	3.250	0.125	3.000	6.32	3.1/4 OD X .125	SEAM			*	*			
82.55	3.60	75.35	3.250	0.142	2.967	7.12	3.1/4 OD X .142	SEAM			*	*	*		
82.55	4.78	72.99	3.250	0.188	2.874	9.31	3.1/40DX .188	SEAM			*	*			
82.55	6.35	69.85	3.250	0.250	2.750	12.12	3.1/4 OD X .250	SEAM			*	*			
83.00	1.50	80.00	3.268	0.059	3.150	3.06		WELD	*	*	*	*	*	*	*
83.00	3.50	76.00	3.268	0.138	2.992	6.97		SEAM			*				

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	316L	310
METRIC		IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 2/3 WEEKS)									
MM	MM	MM	INCH	INCH	INCH										
84.00	2.00	80.00	3.307	0.079	3.150	4.11		WELD	*	*	*	*	*	*	*
84.00	2.00	80.00	3.307	0.079	3.150	4.11		SEAM		*					*
85.00	2.00	81.00	3.346	0.079	3.189	4.16		WELD	*		*	*	*	*	
85.00	2.00	81.00	3.346	0.079	3.189	4.16		SEAM	*					*	
85.00	2.50	80.00	3.346	0.098	3.150	5.16		SEAM	*		*				*
85.00	9.00	67.00	3.346	0.354	2.638	18.50		HBAR	*	*		*			*
85.00	15.00	55.00	3.346	0.591	2.165	28.39		HBAR	*	*					*
85.00	20.00	45.00	3.346	0.787	1.772	35.15		HBAR	*	*	*	*	*	*	*
86.00	3.00	80.00	3.386	0.118	3.150	6.23		SEAM						*	
86.00	7.50	71.00	3.386	0.295	2.795	14.74		SEAM				*			
88.90	1.63	85.64	3.500	0.064	3.372	3.56	3.1/2 OD X .064	WELD	*	*		*	*	*	*
88.90	1.63	85.64	3.500	0.064	3.372	3.56	3.1/2 OD X .064	SEAM		*	*	*	*		
88.90	2.00	84.90	3.500	0.079	3.343	4.35	3.1/2 OD X .079	WELD	*	*	*	*	*	*	*
88.90	2.00	84.90	3.500	0.079	3.343	4.35	3.1/2 OD X .079	SEAM	*	*	*	*	*	*	*
88.90	2.11	84.68	3.500	0.083	3.334	4.59	3 SCH 5	SEAM	*	*	*	*	*	*	*
88.90	2.11	84.68	3.500	0.083	3.334	4.59	3 SCH 5	WELD		*	*	*	*	*	*
88.90	2.30	84.30	3.500	0.091	3.319	4.99	3.1/2 OD X .091	WELD	*		*	*	*	*	
88.90	2.30	84.30	3.500	0.091	3.319	4.99	3.1/2 OD X .091	SEAM			*	*	*	*	
88.90	2.50	83.90	3.500	0.098	3.303	5.41	3.1/2 OD X .098	WELD	*		*	*	*	*	
88.90	2.50	83.90	3.500	0.098	3.303	5.41	3.1/2 OD X .098	SEAM	*		*	*	*	*	*
88.90	2.60	83.70	3.500	0.102	3.295	5.62	3.1/2 OD X .102	WELD	*		*	*	*	*	
88.90	2.60	83.70	3.500	0.102	3.295	5.62	3.1/2 OD X .102	SEAM			*	*	*	*	
88.90	2.90	83.10	3.500	0.114	3.272	6.24	3.1/2 OD X .114	WELD	*		*	*	*	*	
88.90	2.90	83.10	3.500	0.114	3.272	6.24	3.1/2 OD X .114	SEAM	*		*	*	*	*	
88.90	3.05	82.80	3.500	0.120	3.260	6.56	3 SCH 10	WELD	*	*	*	*	*	*	*
88.90	3.05	82.80	3.500	0.120	3.260	6.56	3 SCH 10	SEAM	*	*	*	*	*	*	*
88.90	3.18	82.54	3.500	0.125	3.250	6.83	3.1/2 OD X .125	SEAM			*	*	*	*	
88.90	3.20	82.50	3.500	0.126	3.248	6.87	3.1/2 OD X .126	WELD	*		*	*	*	*	
88.90	3.20	82.50	3.500	0.126	3.248	6.87	3.1/2 OD X .126	SEAM	*		*	*	*	*	
88.90	3.60	81.70	3.500	0.142	3.217	7.69	3.1/2 OD X .142	SEAM	*	*	*	*	*	*	*
88.90	3.60	81.70	3.500	0.142	3.217	7.69	3.1/2 OD X .142	WELD			*	*	*	*	*
88.90	4.05	80.80	3.500	0.159	3.181	8.60	31S0	WELD	*		*	*	*	*	*
88.90	4.05	80.80	3.500	0.159	3.181	8.60	31S0	SEAM	*	*	*	*	*	*	*
88.90	4.50	79.90	3.500	0.177	3.146	9.51	3.1/2 OD X .177	SEAM	*		*	*	*	*	*
88.90	4.78	79.34	3.500	0.188	3.124	10.07	3.1/2 OD X .188	SEAM			*	*	*	*	*
88.90	5.00	78.90	3.500	0.197	3.106	10.50	3.1/2 OD X .197	SEAM			*	*	*	*	*
88.90	5.49	77.92	3.500	0.216	3.068	11.47	3 SCH 40	SEAM	*	*	*	*	*	*	*
88.90	5.49	77.92	3.500	0.216	3.068	11.47	3 SCH 40	WELD		*	*	*	*	*	*
88.90	6.35	76.20	3.500	0.250	3.000	13.13	3.1/2 OD X .250	SEAM			*	*	*	*	*
88.90	7.06	74.78	3.500	0.278	2.944	14.47	3.1/2 OD X .278	SEAM				*	*	*	*
88.90	7.62	73.66	3.500	0.300	2.900	15.51	3 SCH 80	SEAM	*	*	*	*	*	*	*
88.90	9.53	69.84	3.500	0.375	2.750	18.94	3.1/2 OD X .375	SEAM			*	*	*	*	*
88.90	11.13	66.64	3.500	0.438	2.624	21.67	3 SCH 160	SEAM	*	*	*	*	*	*	*
88.90	12.70	63.50	3.500	0.500	2.500	24.23	3.1/2 OD X .500	SEAM			*	*	*	*	*
88.90	15.24	58.42	3.500	0.600	2.300	28.11	3XXS	SEAM		*	*	*	*	*	*
89.00	6.50	76.00	3.504	0.256	2.992	13.43		SEAM	*		*	*	*	*	*
90.00	5.00	80.00	3.543	0.197	3.150	10.64		SEAM			*	*	*	*	*
90.00	9.50	71.00	3.543	0.374	2.795	20.68		HBAR	*	*	*	*	*	*	*
90.00	13.50	63.00	3.543	0.531	2.480	27.93		HBAR	*	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX. 213 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
90.00	13.50	63.00	3.543	0.531	2.480	3368		HBARC	*	*	*	*	*	*	*
90.00	17.00	56.00	3.543	0.669	2.205	33.56		HBAR	*	*	*	*	*	*	*
90.00	17.00	56.00	3.543	0.669	2.205	38.46		HBARC	*	*	*	*	*	*	*
90.00	20.00	50.00	3.543	0.787	1.969	37.86		HBAR	*	*	*	*	*	*	*
90.00	20.00	50.00	3.543	0.787	1.969	37 RF:		HBARC	*	*	*	*	*	*	*
92.00	4.00	84.00	3.622	0.157	3.307	8.81		SEAM				*	*		
93.00	2.00	89.00	3.661	0.079	3.504	4.56		WELD	*						
95.00	2.50	90.00	3.740	0.098	3.543	5.79		SEAM							*
9500	5.00	85.00	3.740	0.197	3.346	11.27		SEAM			*	*	*		
9500	10.00	75.00	3.740	0.394	2.953	22.98		HBAR	*	*					*
95.00	14.00	67.00	3.740	0.551	2.638	3067		HBAR	*	*		*	*	*	*
95.00	14.00	67.00	3.740	0.551	2.638	36.79		HBARC	*	*	*	*	*	*	*
95.00	20.00	55.00	3.740	0.787	2.165	4056		HBAR	*						*
95.00	22.50	50.00	3.740	0.886	1.969	44.12		HBAR	*	*	*	*	*	*	*
95.00	22.50	50.00	3.740	0.886	1.969	48.18		HBARC	*	*	*	*	*	*	*
95.25	6.35	82.55	3.750	0.250	3.250	14.14	3.3/4 OD X .250	SEAM			*				
95.25	11.11	73.03	3.750	0.437	2.875	25.28	3.3/4 OD X .437	HBAR			*				
96.00	15.00	66.00	3.780	0.591	2.598	32.85		HBAR	*			*			
97.00	4.00	89.00	3.819	0.157	3.504	9.31		SEAM	*		*	*	*	*	
10000	2.00	96.00	3.937	0.079	3.780	4.91		WELD	*						
100.00	2.50	95.00	3.937	0.098	3.740	6.10		WELD				*			
10000	3.00	94.00	3.937	0.118	3.701	7.29		SEAM			*		*		
10000	5.00	90.00	3.937	0.197	3.543	11.89		SEAM			*		*		
10000	8.00	84.00	3.937	0.315	3.307	18.4		SEAM			*		*		
10000	10.00	80.00	3.937	0.394	3.150	24.34		HBAR	*	*	*	*	*	*	*
100.00	10.00	80.00	3.937	0.394	3.150	31.96		HBARC	*	*	*	*	*	*	*
100.00	14.50	71.00	3.937	0.571	2.795	3352		HBAR	*	*	*	*	*	*	*
100.00	14.50	71.00	3.937	0.571	2.795	40.02		HBARC	*	*	*	*	*	*	*
10000	18.50	63.00	3.937	0.728	2.480	4077		HBAR	*	*	*	*	*	*	*
10000	18.50	63.00	3.937	0.728	2.480	46.29		HBARC	*	*	*	*	*	*	*
100.00	22.00	56.00	3.937	0.866	2.205	46.41		HBAR	*	*	*	*	*	*	*
100.00	22.00	56.00	3.937	0.866	2.205	51.07		HBARC	*	*	*	*	*	*	*
101.60	1.50	98.60	4.000	0.059	3.882	3.76	4 OD X .059	WELD	*						
10160	1.63	98.34	4.000	0.064	3.872	408	4 OD X .064	WELD	*		*	*			
101.60	1.63	98.34	4.000	0.064	3.872	4.08	4 OD X .064	SEAM	*		*	*			
101.60	2.03	97.54	4.000	0.080	3.840	5.06	4 OD X .080	WELD	*			*			
101.60	2.03	97.54	4.000	0.080	3.840	5.06	4 OD X .080	SEAM	*			*			
10160	2.11	97.38	4.000	0.083	3.834	5.26	3.1/2 SCH 5	WELD		*					*
10160	2.11	97.38	4.000	0.083	3.834	5.26	3.1/2 SCH 5	SEAM			*				*
101.60	3.05	95.50	4.000	0.120	3.760	7.53	3.1/2 SCH 10	WELD	*	*					*
10160	3.05	95.50	4.000	0.120	3.760	7.53	3.1/2 SCH 10	SEAM	*	*	*	*	*	*	*
101.60	3.18	95.24	4.000	0.125	3.750	784	4 OD X .125	SEAM	*		*	*			
101.60	3.60	94.40	4.000	0.142	3.717	8.83	4 OD X .142	SEAM	*	*	*		*	*	
10160	4.05	93.50	4.000	0.159	3.681	9.89	3.1/2 ISO	SEAM	*	*	*		*	*	*
10160	4.78	92.04	4.000	0.188	3.624	11.59	4 OD X .188	SEAM		*			*	*	
101.60	5.00	91.60	4.000	0.197	3.606	12.09	4 OD X .197	SEAM			*		*		

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX. 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
101.60	5.74	90.12	4.000	0.226	3.548	13.78	3.1/2 SCH 40	SEAM	*	*	*	*	*	*	*
101.60	5.74	90.12	4.000	0.226	3.548	13.78	3.1/2 SCH 40	WELD		*					*
101.60	6.35	88.90	4.000	0.250	3.500	15.15	4 OD X .250	SEAM	*		*	*			
101.60	8.08	85.44	4.000	0.318	3.364	18.92	3.1/2 SCH 80	SEAM			*	*			
101.60	9.53	82.54	4.000	0.375	3.250	21.97	4 OD X .375	SEAM			*				
101.60	11.00	79.60	4.000	0.433	3.134	24.95	4 OD X .433	SEAM			*				
101.60	12.70	76.20	4.000	0.500	3.000	28.27	4 OD X .500	SEAM			*	*			
<hr/>															
102.00	3.00	96.00	4.016	0.118	3.780	7.44		SEAM			*				
102.00	3.50	95.00	4.016	0.138	3.740	8.63		SEAM	*		*		*	*	*
102.00	6.50	89.00	4.016	0.256	3.504	15.54		SEAM			*		*		
<hr/>															
103.00	1.50	100.00	4.055	0.059	3.937	3.81		WELD	*	*	*	*	*	*	*
<hr/>															
104.00	2.00	100.00	4.094	0.079	3.937	5.11		WELD	*	*	*	*	*	*	*
104.00	6.00	92.00	4.094	0.236	3.622	14.72		SEAM			*		*		
<hr/>															
105.00	2.50	100.00	4.134	0.098	3.937	6.42		WELD	*			*			
105.00	2.50	100.00	4.134	0.098	3.937	6.42		SEAM			*				
<hr/>															
106.00	2.75	100.50	4.173	0.108	3.957	7.11		WELD	*						
106.00	2.80	100.40	4.173	0.110	3.953	7.24		SEAM	*		*				
106.00	3.00	100.00	4.173	0.118	3.937	7.74		WELD	*		*	*	*		
106.00	10.50	85.00	4.173	0.413	3.346	27.12		HBAR	*		*				
106.00	13.00	80.00	4.173	0.512	3.150	32.69		HBAR	*	*	*		*		
106.00	13.00	80.00	4.173	0.512	3.150	40.16		HBARC	*	*	*		*		
106.00	17.50	71.00	4.173	0.689	2.795	41.88		HBAR	*	*	*		*		
106.00	17.50	71.00	4.173	0.689	2.795	48.22		HBARC	*	*	*		*		
106.00	21.50	63.00	4.173	0.846	2.480	49.13		HBAR	*	*	*		*		
106.00	21.50	63.00	4.173	0.846	2.480	54.48		HBARC	*	*	*		*		
106.00	25.00	56.00	4.173	0.984	2.205	54.77		HBAR	*	*	*		*		
106.00	25.00	56.00	4.173	0.984	2.205	59.26		HBARC	*	*	*		*		
<hr/>															
108.00	2.00	104.00	4.252	0.079	4.094	5.31	4.1/4 OD X .079	WELD	*		*	*	*	*	*
108.00	2.50	103.00	4.252	0.098	4.055	6.60	4.1/4 OD X .098	WELD			*	*	*	*	*
108.00	2.60	102.80	4.252	0.102	4.047	6.86	4.1/4 OD X .102	WELD			*	*	*	*	*
108.00	2.90	102.20	4.252	0.114	4.024	7.63	4.1/4 OD X .114	WELD			*	*	*	*	*
108.00	2.90	102.20	4.252	0.114	4.024	7.63	4.1/40DX.114	SEAM			*	*	*	*	*
108.00	3.00	102.00	4.252	0.118	4.016	7.89	4.1/4 OD X .118	WELD	*		*	*	*	*	*
108.00	3.00	102.00	4.252	0.118	4.016	7.89	4.1/4 OD X .118	SEAM	*		*	*	*	*	*
108.00	3.18	101.64	4.252	0.125	4.002	8.35	4.1/4 OD X .125	SEAM	*		*	*	*	*	*
108.00	3.60	100.80	4.252	0.142	3.969	9.41	4.1/4 OD X .142	SEAM	*	*	*	*	*	*	*
108.00	4.00	100.00	4.252	0.157	3.937	10.42	4.1/4 OD X .157	WELD	*		*	*	*	*	*
108.00	4.00	100.00	4.252	0.157	3.937	10.42	4.1/4 OD X .157	SEAM	*	*	*	*	*	*	*
108.00	4.50	99.00	4.252	0.177	3.898	11.66	4.1/4 OD X .177	SEAM			*	*	*	*	*
108.00	5.00	98.00	4.252	0.197	3.858	12.90	4.1/4 OD X .197	SEAM			*	*	*	*	*
108.00	5.40	97.20	4.252	0.213	3.827	13.87	4.1/4 OD X .213	SEAM			*	*	*	*	*
108.00	6.30	95.40	4.252	0.248	3.756	16.04	4.1/40DX.248	SEAM		*	*	*	*	*	*
108.00	6.35	95.30	4.252	0.250	3.752	16.16	4.1/4 OD X .250	SEAM			*	*	*	*	*
108.00	8.00	92.00	4.252	0.315	3.622	20.03	4.1/4 OD X .315	SEAM			*	*	*	*	*
108.00	12.50	83.00	4.252	0.492	3.268	32.28	4.1/4 OD X .492	HBAR	*						
<hr/>															
109.00	14.80	79.40	4.291	0.583	3.126	37.70		HBAR							*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)					
MM	MM	MM	INCH	INCH	INCH									
112.00	4.00	104.00	4409	0157	4.094	10.82		SEAM			*			
112.00	6.00	100.00	4.409	0.236	3.937	15.93		SEAM	*				*	
112.00	7.50	97.00	4409	0.295	3.819	21.20		HBAR			*			
112.00	8.00	96.00	4.409	0.315	3.780	20.83		SEAM			*		*	
112.00	11.00	90.00	4409	0.433	3.543	30.05		HBAR	*	*	*	*		*
112.00	16.00	80.00	4409	0.630	3.150	41.54		HBAR	*	*	*	*		*
112.00	16.00	80.00	4.409	0.630	3.150	48.83		HBARC	*	*	*	*		*
112.00	20.50	71.00	4409	0.807	2.795	5073		HBAR	*	*	*	*		*
112.00	20.50	71.00	4409	0.807	2.795	56.90		HBARC	*	*	*	*		*
11200	24.50	63.00	4409	0.965	2480	5797		HBAR	*	*	*	*		*
112.00	24.50	63.00	4409	0.965	2480	63.17		HBARC	*	*	*	*		*
112.00	28.00	5600	4409	1.102	2.205	67.95		HBARC	*	*	*	*		*
114.30	1.60	111.10	4.500	0.063	4.374	4.52	4.1/2 OD X .063	WELD	*	*				*
114.30	2.00	11030	4500	0.079	4.343	5.62	4.1/2 OD X .079	WELD	*	*	*	*	*	*
114.30	2.11	110.08	4.500	0.083	4.334	5.93	4 SCH 5	WELD		*	*			*
114.30	2.11	110.08	4.500	0083	4.334	5.93	4 SCH 5	SEAM		*	*			*
11430	2.60	109.10	4.500	0102	4.295	7.27	4.1/2 OD X .102	WELD	*	*	*		*	*
114.30	2.60	109.10	4.500	0102	4.295	727	4.1/2 OD X .102	SEAM	*	*	*		*	*
114.30	2.90	108.50	4500	0.114	4.272	8.09	4.1/2 OD X .114	WELD	*		*		*	
11430	2.90	10850	4.500	0.114	4.272	8.09	4.1/2 OD X .114	SEAM					*	
114.30	3.00	108.30	4.500	0.118	4.264	8.36	4.1/2 OD X .118	WELD		*				*
11430	3.05	108.20	4.500	0120	4.260	8.50	4 SCH 10	WELD	*	*	*	*	*	*
114.30	3.05	10820	4.500	0.120	4260	8.50	4 SCH 10	SEAM	*	*	*	*	*	*
114.30	3.20	107.90	4500	0.126	4.248	8.90	4.1/2 OD X .126	WELD	*		*		*	
114.30	3.20	10790	4500	0126	4.248	8.90	4.1/2 OD X .126	SEAM	*		*		*	
114.30	360	10710	4500	0.142	4.217	998	4.1/2 OD X .142	WELD	*		*		*	
11430	3.60	10710	4500	0.142	4217	998	4.1/2 OD X .142	SEAM	*		*		*	
11430	4.00	106.30	4500	0157	4185	1105	4.1/2 OD X .157	WELD			*		*	
114.30	405	106.20	4.500	0.159	4.181	11.18	4.1/2 OD X .159	SEAM					*	
114.30	4.50	105.30	4.500	0.177	4.146	12.37	41S0	WELD	*		*			
11430	450	105.30	4500	0.177	4.146	12.37	41S0	SEAM	*	*	*		*	*
114.30	4.78	104.74	4.500	0188	4.124	13.11	4.1/2 OD X .188	SEAM	*		*			
114.30	5.40	103.50	4.500	0213	4.075	14.73	4.1/2 OD X .213	SEAM	*		*		*	
11430	602	102.26	4.500	0.237	4.026	16.32	4 SCH 40	SEAM	*	*	*	*	*	*
114.30	602	102.26	4.500	0.237	4.026	1632	4 SCH 40	WELD		*	*			*
114.30	6.35	101.60	4.500	0.250	4.000	1716	4.1/2 OD X .250	SEAM			*	*		
114.30	7.10	100.10	4.500	0.280	3.941	19.06	4.1/2 OD X .280	SEAM				*	*	
114.30	8.56	97.18	4.500	0.337	3.826	22.66	4 SCH 80	SEAM	*	*	*	*	*	*
114.30	8.56	97.18	4.500	0.337	3.826	22.66	4 SCH 80	WELD						*
114.30	12.70	88.90	4.500	0.500	3.500	32.31	4.1/2 OD X .500	SEAM			*			
114.30	1349	87.32	4.500	0.531	3.438	34.05	4 SCH 160	SEAM	*	*	*	*	*	*
11430	1349	87.32	4.500	0.531	3.438	44.94	4 SCH 160	HBARC	*	*	*	*	*	*
114.30	17.12	8006	4.500	0.674	3.152	52.24	4XXS	HBARC	*	*	*	*	*	*
11430	17.12	80.06	4.500	0.674	3.152	41.66	4XXS	SEAM		*	*	*	*	*
114.30	19.05	76.20	4.500	0.750	3.000	45.44	4.1/2X.750	SEAM				*		
118.00	14.00	90.00	4.646	0.551	3.543	39.38		HBAR	*	*	*	*	*	*
118.00	19.00	80.00	4.646	0.748	3.150	50.87		HBAR	*	*	*	*	*	*
118.00	19.00	80.00	4.646	0748	3.150	57.99		HBARC	*	*	*	*	*	*
11800	23.50	7100	4.646	0.925	2.795	6006		HBAR	*	*	*	*	*	*
118.00	23.50	71.00	4646	0.925	2.795	66.06		HBARC	*	*	*	*	*	*
118.00	27.50	63.00	4.646	1.083	2480	67.31		HBAR	*	*	*	*	*	*
118.00	27.50	63.00	4.646	1.083	2480	72.32		HBARC	*	*	*	*	*	*



TELEPHONE: 01207 690066

FAX 01207 690069

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC		IMPERIAL			KGS/MTR		* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
118.00	31.00	56.00	4.646	1.220	2.205	77.10		HBARC	*	*	*	*	*	*	*
121.00	4.00	113.00	4.764	0.157	4.449	11.72		SEAM		*	*	*	*	*	*
125.00	12.50	100.00	4.921	0.492	3.937	38.03		HBAR	*	*	*	*	*	*	*
125.00	17.50	90.00	4.921	0.689	3.543	50.88		HBAR	*	*	*	*	*	*	*
125.00	17.50	90.00	4.921	0.689	3.543	59.06		HBARC	*	*	*	*	*	*	*
125.00	20.00	85.00	4.921	0.787	3.346	64.34		HBARC	*	*	*	*	*	*	*
125.00	22.50	80.00	4.921	0.886	3.150	62.37		HBAR	*	*	*	*	*	*	*
125.00	22.50	80.00	4.921	0.886	3.150	69.28		HBARC	*	*	*	*	*	*	*
125.00	25.00	75.00	4.921	0.984	2.953	73.89		HBARC	*	*	*	*	*	*	*
125.00	27.00	71.00	4.921	1.063	2.795	71.56		HBAR	*	*	*	*	*	*	*
125.00	27.00	71.00	4.921	1.063	2.795	77.35		HBARC	*	*	*	*	*	*	*
125.00	31.00	63.00	4.921	1.220	2.480	83.61		HBARC	*	*	*	*	*	*	*
127.00	1.63	123.74	5.000	0.064	4.872	5.12	5 OD X .064	WELD	*		*	*	*	*	*
127.00	3.23	120.54	5.000	0.127	4.746	10.01	5 OD X .128	SEAM		*					*
127.00	4.00	119.00	5.000	0.157	4.685	12.32	5 OD X .157	SEAM			*		*	*	*
127.00	4.78	117.44	5.000	0.188	4.624	14.63	5 OD X .188	SEAM			*		*	*	*
127.00	5.00	117.00	5.000	0.197	4.606	15.27	5 OD X .197	SEAM			*		*	*	*
127.00	6.35	114.30	5.000	0.250	4.500	19.18	5 OD X .250	SEAM		*	*	*	*	*	*
127.00	9.53	107.94	5.000	0.375	4.250	28.03	5 OD X .375	SEAM		*	*	*	*	*	*
127.00	12.70	101.60	5.000	0.500	4.000	36.35	5 OD X .500	SEAM			*	*	*	*	*
128.00	1.50	125.00	5.039	0.059	4.921	4.75		WELD	*		*	*	*	*	*
129.00	2.00	125.00	5.079	0.079	4.921	6.36		WELD	*	*	*	*	*	*	*
132.00	13.00	106.00	5.197	0.512	4.173	41.84		HBAR	*	*	*	*	*	*	*
132.00	13.00	106.00	5.197	0.512	4.173	51.89		HBARC	*	*	*	*	*	*	*
132.00	18.50	95.00	5.197	0.728	3.740	65.39		HBARC	*	*	*	*	*	*	*
132.00	21.00	90.00	5.197	0.827	3.543	63.04		HBAR	*	*	*	*	*	*	*
132.00	21.00	90.00	5.197	0.827	3.543	71.00		HBARC	*	*	*	*	*	*	*
132.00	23.50	85.00	5.197	0.925	3.346	76.28		HBARC	*		*	*	*	*	*
132.00	26.00	80.00	5.197	1.024	3.150	74.53		HBAR	*	*	*	*	*	*	*
132.00	26.00	80.00	5.197	1.024	3.150	81.22		HBARC	*	*	*	*	*	*	*
132.00	28.50	75.00	5.197	1.122	2.953	79.77		HBAR		*					
132.00	30.50	71.00	5.197	1.201	2.795	83.72		HBAR	*	*	*	*	*	*	*
132.00	30.50	71.00	5.197	1.201	2.795	89.28		HBARC	*	*	*	*	*	*	*
133.00	2.00	129.00	5.236	0.079	5.079	6.56		WELD			*		*	*	*
133.00	2.50	128.00	5.236	0.098	5.039	8.17		WELD			*		*	*	*
133.00	3.00	127.00	5.236	0.118	5.000	9.77		SEAM	*		*		*	*	*
133.00	3.00	127.00	5.236	0.118	5.000	9.77		WELD			*		*	*	*
133.00	4.00	125.00	5.236	0.157	4.921	12.92		SEAM	*	*	*		*	*	*
133.00	4.00	125.00	5.236	0.157	4.921	12.92		WELD			*		*	*	*
133.00	5.00	123.00	5.236	0.197	4.843	16.03		SEAM			*		*	*	*
133.00	6.30	120.40	5.236	0.248	4.740	19.99		SEAM			*		*	*	*
133.00	11.00	111.00	5.236	0.433	4.370	33.60		SEAM			*		*	*	*
133.00	14.20	104.60	5.236	0.559	4.118	42.24		SEAM			*		*	*	*
137.90	16.30	105.30	5.429	0.642	4.146	53.60		HBAR							*
139.70	2.00	135.70	5.500	0.079	5.343	6.90	5.1/2 OD X .079	WELD	*	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC		IMPERIAL			KGS/MTR		* = EX STOCK (OR MAX 2/3 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
13970	2.60	134.50	5.500	0.102	5.295	8.93	5.1/2 OD X .102	WELD	*	*	*	*	*	*	*
139.70	2.90	133.90	5.500	0.114	5.272	9.93	5.1/2 OD X .114	WELD			*	*	*	*	*
139.70	3.00	133.70	5.500	0.118	5.264	10.27	5.1/2 OD X .118	WELD	*	*	*	*	*	*	*
139.70	3.18	133.34	5.500	0.125	5.250	10.87	5.1/2 OD X .125	SEAM			*	*	*	*	*
139.70	3.20	133.30	5.500	0.126	5.248	10.94	5.1/2 OD X .126	WELD			*	*	*	*	*
139.70	4.00	131.70	5.500	0.157	5.185	13.59	5.1/2 OD X .157	SEAM	*	*	*	*	*	*	*
139.70	4.00	131.70	5.500	0.157	5.185	13.59	5.1/2 OD X .157	WELD			*	*	*	*	*
139.70	5.00	129.70	5.500	0.197	5.106	16.86	5.1/2 OD X .197	SEAM			*	*	*	*	*
13970	6.35	127.00	5.500	0.250	5.000	21.20	5.1/2 OD X .250	SEAM				*	*	*	*
139.70	7.10	125.50	5.500	0.280	4.941	23.57	5.1/2 OD X .280	SEAM			*	*	*	*	*
139.70	9.53	120.64	5.500	0.375	4.750	31.06	5.1/2 OD X .375	SEAM			*	*	*	*	*
139.70	10.00	119.70	5.500	0.394	4.713	32.48	5.1/2 OD X .394	SEAM				*	*	*	*
13970	12.70	114.30	5.500	0.500	4.500	40.39	5.1/2 OD X .500	SEAM			*	*	*	*	*
<hr/>															
140.00	14.00	112.00	5.512	0.551	4.409	47.70		HBAR	*	*	*	*	*	*	*
140.00	14.00	112.00	5.512	0.551	4.409	58.29		HBARC	*	*	*	*	*	*	*
14000	20.00	100.00	5.512	0.787	3.937	64.91		HBAR	*	*	*	*	*	*	*
14000	20.00	100.00	5.512	0.787	3.937	73.89		HBARC	*	*	*	*	*	*	*
140.00	22.50	95.00	5.512	0.886	3.740	79.83		HBARC	*	*	*	*	*	*	*
140.00	25.00	90.00	5.512	0.984	3.543	77.75		HBAR	*	*	*	*	*	*	*
140.00	25.00	9000	5.512	0.984	3.543	85.44		HBARC	*	*	*	*	*	*	*
140.00	27.50	85.00	5.512	1.083	3.346	90.71		HBARC	*	*	*	*	*	*	*
140.00	30.00	80.00	5.512	1.181	3.150	89.24		HBAR	*	*	*	*	*	*	*
140.00	30.00	80.00	5.512	1.181	3.150	95.65		HBARC	*	*	*	*	*	*	*
140.00	34.50	7100	5.512	1.358	2.795	103.72		HBARC	*	*	*	*	*	*	*
<hr/>															
14130	200	13730	5.563	0.079	5.406	6.98		WELD		*					
14130	2.77	13576	5.563	0.109	5.345	961	5 SCH 5	WELD		*	*				*
14130	3.00	135.30	5.563	0.118	5.327	10.39		WELD	*						
14130	3.40	13450	5.563	0.134	5.295	11.74	5 SCH 10	SEAM	*	*	*		*	*	*
141.30	3.40	13450	5.563	0.134	5.295	11.74	5 SCH 10	WELD		*	*				*
141.30	6.55	128.20	5.563	0.258	5.047	22.10	5 SCH 40	SEAM	*	*	*	*	*	*	*
14130	9.52	122.26	5.563	0.375	4.813	31.41	5 SCH 80	SEAM	*	*	*	*	*	*	*
141.30	15.88	109.54	5.563	0.625	4.313	64.07	5 SCH 160	HBARC	*	*	*	*	*	*	*
141.30	15.88	109.54	5.563	0.625	4.313	49.87	5 SCH 160	SEAM							*
14130	1905	103.20	5.563	0.750	4.063	72.35	5 XXS	HBARC	*	*	*	*	*	*	*
<hr/>															
150.00	12.50	125.00	5.906	0.492	4.921	46.48		HBAR	*	*	*	*	*	*	*
150.00	1900	112.00	5.906	0.748	4.409	77.53		HBARC	*	*	*	*	*	*	*
15000	22.00	106.00	5.906	0.866	4.173	76.15		HBAR	*	*	*	*	*	*	*
15000	22.00	10600	5.906	0.866	4.173	85.57		HBARC	*	*	*	*	*	*	*
15000	2500	100.00	5.906	0.984	3.937	84.51		HBAR	*						
150.00	27.50	9500	5.906	1.083	3.740	91.10		HBAR	*	*	*	*	*	*	*
150.00	27.50	95.00	5.906	1.083	3.740	99.08		HBARC	*	*	*	*	*	*	*
150.00	30.00	90.00	5.906	1.181	3.543	104.69		HBARC	*	*	*	*	*	*	*
150.00	32.50	85.00	5.906	1.280	3.346	109.95		HBARC	*	*	*	*	*	*	*
150.00	35.00	8000	5.906	1.378	3.150	108.85		HBAR	*	*	*	*	*	*	*
150.00	35.00	8000	5.906	1.378	3.150	114.90		HBARC	*	*	*	*	*	*	*
15000	39.50	71.00	5.906	1.555	2.795	122.96		HBARC	*	*	*	*	*	*	*
<hr/>															
15180	1588	120.04	5.976	0.625	4.726	58.37		HBAR		*					
<hr/>															
152.40	1.63	149.14	6.000	0.064	5.872	6.15	6 OD X .064	WELD	*		*	*			
152.40	3.23	145.94	6.000	0.127	5.746	12.06	6 OD X .128	SEAM		*					*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC			IMPERIAL			KGS/MTR			"= EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
152.40	6.35	139.70	6.000	0.250	5.500	23.22	6 OD X .250	SEAM	"	"	"	"	"	"	"
152.40	7.00	138.40	6.000	0.276	5.449	25.49	6 OD X .276	SEAM	"	"	"	"	"	"	"
152.40	7.50	137.40	6.000	0.295	5.409	27.21	6 OD X .295	SEAM	"	"	"	"	"	"	"
152.40	9.53	133.34	6.000	0.375	5.250	34.09	6 OD X .375	SEAM	"	"	"	"	"	"	"
152.40	12.70	127.40	6.000	0.500	5.000	44.43	6 OD X .500	SEAM	"	"	"	"	"	"	"
153.00	1.50	150.00	6.024	0.059	5.906	5.69		WELD	"	"	"	"	"	"	"
154.00	2.00	150.00	6.063	0.079	5.906	7.61		WELD	"	"	"	"	"	"	"
155.00	21.50	112.00	6.102	0.846	4.409	87.65		HBARC	"	"	"	"	"	"	"
155.00	24.50	106.00	6.102	0.965	4.173	95.70		HBARC	"	"	"	"	"	"	"
155.00	30.00	95.00	6.102	1.181	3.740	109.19		HBARC	"	"	"	"	"	"	"
155.00	32.50	90.00	6.102	1.280	3.543	114.80		HBARC	"	"	"	"	"	"	"
155.00	35.00	85.00	6.102	1.378	3.346	120.08		HBARC	"	"	"	"	"	"	"
155.00	37.50	80.00	6.102	1.476	3.150	125.02		HBARC	"	"	"	"	"	"	"
155.00	42.00	71.00	6.102	1.654	2.795	133.08		HBARC	"	"	"	*	*	*	*
156.00	3.00	150.00	6.142	0.118	5.906	11.49		WELD	"	"	"	"	"	"	"
158.00	4.00	150.00	6.220	0.157	5.906	15.42		WELD	"	"	"	"	"	"	"
159.00	2.00	155.00	6.260	0.079	6.102	7.86		WELD	"	"	"	"	"	"	"
159.00	2.50	154.00	6.260	0.098	6.063	9.80		WELD	"	"	"	"	"	"	"
159.00	2.60	153.80	6.260	0.102	6.055	10.18		WELD	"	"	"	"	"	"	"
159.00	3.00	153.00	6.260	0.118	6.024	11.72		WELD	"	"	"	"	"	"	"
159.00	4.00	151.00	6.260	0.157	5.945	15.52		WELD	"	"	*	"	"	"	"
159.00	4.50	150.00	6.260	0.177	5.906	17.41		SEAM	"	"	"	"	"	"	*
159.00	5.00	149.00	6.260	0.197	5.866	19.28		WELD	"	"	*	"	"	"	"
159.00	6.30	146.40	6.260	0.248	5.764	24.09		SEAM	"	"	"	"	"	"	"
159.00	7.50	144.00	6.260	0.295	5.669	28.45		SEAM	"	"	"	"	"	"	"
159.00	8.00	143.00	6.260	0.315	5.630	30.25		SEAM	"	"	*	"	"	"	"
159.40	8.00	143.40	6.276	0.315	5.646	30.33		SEAM	"	"	"	"	"	"	"
159.40	12.50	134.40	6.276	0.492	5.291	45.98		SEAM	"	"	"	"	"	"	"
160.00	14.00	132.00	6.299	0.551	5.197	55.27		HBAR	"	"	"	"	"	"	"
160.00	14.00	132.00	6.299	0.551	5.197	67.84		HBARC	"	"	"	"	"	"	"
160.00	16.50	127.00	6.299	0.650	5.000	75.91		HBARC	"	"	"	"	"	"	"
160.00	19.00	122.00	6.299	0.748	4.803	72.45		HBAR	"	"	"	"	"	"	"
160.00	19.00	122.00	6.299	0.748	4.803	83.63		HBARC	"	"	"	"	"	"	"
160.00	20.00	120.00	6.299	0.787	4.724	75.72		HBAR	"	"	"	"	"	"	"
160.00	24.00	112.00	6.299	0.945	4.409	88.27		HBAR	"	"	"	*	"	"	"
160.00	24.00	112.00	6.299	0.945	4.409	98.10		HBARC	"	"	"	"	"	"	"
160.00	27.50	105.00	6.299	1.083	4.134	107.44		HBARC	"	"	"	"	"	"	"
160.00	30.00	100.00	6.299	1.181	3.937	113.71		HBARC	"	"	"	"	"	"	"
160.00	32.50	95.00	6.299	1.280	3.740	119.64		HBARC	"	"	"	"	"	"	"
160.00	35.00	90.00	6.299	1.378	3.543	118.31		HBAR	"	"	"	"	"	"	"
160.00	35.00	90.00	6.299	1.378	3.543	125.25		HBARC	"	"	"	"	"	"	"
160.00	37.50	85.00	6.299	1.476	3.346	130.53		HBARC	"	"	"	"	"	"	*
160.00	40.00	80.00	6.299	1.575	3.150	135.47		HBARC	"	"	"	"	"	"	"
165.00	16.50	132.00	6.496	0.650	5.197	78.62		HBARC	"	"	"	"	"	"	"
165.00	21.50	122.00	6.496	0.846	4.803	94.41		HBARC	"	"	"	"	"	"	"



STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)					
MM	MM	MM	INCH	INCH	INCH									
165.00	26.50	112.00	6.496	1.043	4.409	108.88		HBARC	*	*	*	*	*	*
165.00	30.00	105.00	6.496	1.181	4.134	118.22		HBARC	*	*	*	*	*	*
165.00	32.50	100.00	6.496	1.280	3.937	124.49		HBARC	*	*	*	*	*	*
165.00	35.00	95.00	6.496	1.378	3.740	130.43		HBARC	*	*	*	*	*	*
165.00	37.50	90.00	6.496	1.476	3.543	136.04		HBARC	*	*	*	*	*	*
165.00	40.00	85.00	6.496	1.575	3.346	141.31		HBARC	*	*	*	*	*	*
165.00	42.50	80.00	6.496	1.673	3.150	146.26		HBARC	*	*	*	*	*	*
165.10	6.35	152.40	6.500	0.250	6.000	25.24	6.1/2 OD X .250	SEAM			*	*		
165.10	12.70	139.70	6.500	0.500	5.500	48.46	6.1/2 OD X .500	SEAM			*			
168.30	2.00	164.30	6.626	0.079	6.469	8.33		WELD	*	*	*	*	*	*
168.30	2.60	163.10	6.626	0.102	6.421	10.79		WELD	*	*	*	*	*	*
168.30	2.77	162.76	6.626	0.109	6.408	11.48	6 SCH 5	WELD	*	*	*	*	*	*
168.30	3.00	162.30	6.626	0.118	6.390	12.42		WELD	*	*	*	*	*	*
168.30	3.40	161.50	6.626	0.134	6.358	14.04	6 SCH 10	WELD	*	*	*	*	*	*
168.30	3.40	161.50	6.626	0.134	6.358	14.04	6 SCH 10	SEAM	*	*	*	*	*	*
168.30	4.00	160.30	6.626	0.157	6.311	16.46		WELD	*	*	*	*	*	*
168.30	4.50	159.30	6.626	0.177	6.272	18.46		SEAM	*	*	*	*	*	*
168.30	5.00	158.30	6.626	0.197	6.232	20.45		SEAM	*	*	*	*	*	*
168.30	5.00	158.30	6.626	0.197	6.232	20.45		WELD	*	*	*	*	*	*
168.30	6.00	156.30	6.626	0.236	6.154	24.38		WELD	*	*	*	*	*	*
168.30	7.11	154.08	6.626	0.280	6.066	28.70	6 SCH 40	SEAM	*	*	*	*	*	*
168.30	7.11	154.08	6.626	0.280	6.066	28.70	6 SCH 40	WELD	*	*	*	*	*	*
168.30	8.00	152.30	6.626	0.315	5.996	32.11		SEAM	*	*	*	*	*	*
168.30	8.08	152.14	6.626	0.318	5.990	32.42		SEAM	*	*	*	*	*	*
168.30	9.53	149.24	6.626	0.375	5.876	37.89		SEAM	*	*	*	*	*	*
168.30	10.97	146.36	6.626	0.432	5.762	43.22	6 SCH 80	SEAM	*	*	*	*	*	*
168.30	10.97	146.36	6.626	0.432	5.762	43.22	6 SCH 80	WELD	*	*	*	*	*	*
168.30	14.27	139.76	6.626	0.562	5.502	55.04	6 SCH 120	SEAM	*	*	*	*	*	*
168.30	14.27	139.76	6.626	0.562	5.502	72.76	6 SCH 120	HBARC	*	*	*	*	*	*
168.30	15.39	137.52	6.626	0.606	5.414	58.93		SEAM	*	*	*	*	*	*
168.30	17.50	133.30	6.626	0.689	5.248	66.08		SEAM	*	*	*	*	*	*
168.30	18.23	131.84	6.626	0.718	5.191	68.50	6 SCH 160	SEAM	*	*	*	*	*	*
168.30	18.24	131.82	6.626	0.718	5.190	86.22	6 SCH 160	HBARC	*	*	*	*	*	*
168.30	20.00	128.30	6.626	0.787	5.051	74.27		SEAM	*	*	*	*	*	*
168.30	21.95	124.40	6.626	0.864	4.898	98.05	6XXS	HBARC	*	*	*	*	*	*
168.30	21.95	124.40	6.626	0.864	4.898	80.44	6 XXS	SEAM	*	*	*	*	*	*
168.30	22.00	124.30	6.626	0.866	4.894	80.59		SEAM	*	*	*	*	*	*
170.00	15.00	140.00	6.693	0.591	5.512	62.88		HBAR	*	*	*	*	*	*
17000	15.00	14000	6.693	0.591	5512	7615		HBARC	*	*	*	*	*	*
170.00	20.00	130.00	6.693	0.787	5.118	81.13		HBAR	*	*	*	*	*	*
170.00	20.00	130.00	6.693	0.787	5.118	93.00		HBARC	*	*	*	*	*	*
170.00	22.50	125.00	6.693	0.886	4.921	100.93		HBARC	*	*	*	*	*	*
170.00	26.00	118.00	6.693	1.024	4.646	101.25		HBAR	*	*	*	*	*	*
170.00	26.00	118.00	6.693	1.024	4.646	111.48		HBARC	*	*	*	*	*	*
17000	30.00	110.00	6.693	1.181	4.331	122.73		HBARC	*	*	*	*	*	*
17000	32.00	106.00	6.693	1.260	4.173	128.04		HBARC	*	*	*	*	*	*
170.00	32.00	106.00	6.693	1.260	4.173	119.43		HBAR	*	*	*	*	*	*
17000	32.50	105.00	6.693	1.280	4.134	120.85		HBAR	*	*	*	*	*	*
170.00	35.00	100.00	6.693	1.378	3.937	127.77		HBAR	*	*	*	*	*	*
170.00	35.00	100.00	6.693	1.378	3.937	135.61		HBARC	*	*	*	*	*	*
170.00	37.50	95.00	6.693	1.476	3.740	141.54		HBARC	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316316Ti316L	310
METRIC		IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 2/3 WEEKS)							
MM	MM	MM	INCH	INCH	INCH								
170.00	40.00	90.00	6.693	1.575	3.543	147.15		HBARC	*	*	*	*	*
177.80	6.35	165.10	7.000	0.250	6.500	27.26	7 OD X .250	SEAM					*
177.80	12.00	153.80	7.000	0.472	6.055	49.82	70DX.472	SEAM					*
177.80	12.70	152.40	7.000	0.500	6.000	52.50	7 OD X .1/2	SEAM		*			
180.00	15.00	150.00	7.087	0.591	5.906	66.93		HBAR	*	*	*	*	*
18000	15.00	150.00	7.087	0.591	5.906	81.20		HBARC	●	*	*	*	*
180.00	20.00	140.00	7.087	0.787	5.512	86.54		HBAR	*	*		*	*
180.00	20.00	140.00	7.087	0.787	5.512	99.38		HBARC	*	*	*	●	*
180.00	25.00	130.00	7.087	0.984	5.118	116.23		HBARC	*	*	*	●	*
180.00	27.50	125.00	7.087	1.083	4.921	113.41		HBAR	*	*	*	●	*
180.00	27.50	125.00	7.087	1.083	4.921	124.16		HBARC	*	*	*	*	*
180.00	30.00	120.00	7.087	1.181	4.724	131.76		HBARC	*	*	*	●	*
180.00	34.00	112.00	7.087	1.339	4.409	143.23		HBARC	*	*	*	*	*
180.00	40.00	100.00	7.087	1.575	3.937	158.83		HBARC	*	*	*	*	*
180.00	40.00	100.00	7.087	1.575	3.937	151.44		HBAR		*			*
180.00	45.00	90.00	7.087	1.772	3.543	170.37		HBARC	*	*	*	*	*
185.00	17.50	150.00	7.283	0.689	5.906	93.30		HBARC	●	*	*	*	*
185.00	22.50	140.00	7.283	0.886	5.512	111.48		HBARC	●	●	*	*	*
185.00	27.50	130.00	7.283	1.083	5.118	128.33		HBARC	*	*	*	*	*
185.00	30.00	125.00	7.283	1.181	4.921	136.27		HBARC	*	*	*	*	●
185.00	32.50	120.00	7.283	1.280	4.724	143.86		HBARC	*	*	*	*	*
185.00	36.50	112.00	7.283	1.437	4.409	155.33		HBARC	*	*	*	*	*
185.00	42.50	100.00	7.283	1.673	3.937	170.94		HBARC	*	*	*	*	●
185.00	47.50	90.00	7.283	1.870	3.543	182.49		HBARC	*	*	*	*	*
190.00	15.00	160.00	7.480	0.591	6.299	70.99		HBAR	*	*	*	*	*
190.00	15.00	160.00	7.480	0.591	6.299	86.23		HBARC	*	●	*	*	*
190.00	20.00	150.00	7.480	0.787	5.906	91.95		HBAR	*	*	*	*	●
190.00	20.00	150.00	7.480	0.787	5.906	105.75		HBARC	*	●	*	*	*
190.00	25.00	140.00	7.480	0.984	5.512	111.55		HBAR	*				
190.00	25.00	140.00	7.480	0.984	5.512	123.92		HBARC	*	*	*	*	●
190.00	29.00	132.00	7.480	1.142	5.197	126.26		HBAR	*	*	*	*	●
190.00	29.00	132.00	7.480	1.142	5.197	137.51		HBARC	*	*	*	*	*
190.00	30.00	130.00	7.480	1.181	5.118	129.81		HBAR		*			
190.00	32.50	125.00	7.480	1.280	4.921	148.71		HBARC	*	*	*	●	*
190.00	35.00	120.00	7.480	1.378	4.724	156.31		HBARC	*	*	*	●	*
190.00	40.00	110.00	7.480	1.575	4.331	170.51		HBARC	*	*	*	●	●
190.00	42.00	106.00	7.480	1.654	4.173	168.10		HBAR		*			●
190.00	45.00	100.00	7.480	1.772	3.937	183.38		HBARC	*	*	●	●	*
193.70	8.00	177.70	7.626	0.315	6.996	37.20		SEAM			*		
193.70	8.10	177.50	7.626	0.319	6.988	37.64		SEAM		*			
200.00	15.00	170.00	7.874	0.591	6.693	75.05		HBAR	*				
200.00	20.00	160.00	7.874	0.787	6.299	97.35		HBAR	*	*	*	*	●
200.00	20.00	160.00	7.874	0.787	6.299	112.12		HBARC	*	*	*	●	*
200.00	25.00	150.00	7.874	0.984	5.906	118.31		HBAR	*	*		*	*
200.00	25.00	150.00	7.874	0.984	5.906	131.62		HBARC	*	*	*	●	*
200.00	30.00	140.00	7.874	1.181	5.512	137.92		HBAR	*	*	*	●	*
200.00	30.00	140.00	7.874	1.181	5.512	149.81		HBARC	*	*	*	*	*
200.00	35.00	130.00	7.874	1.378	5.118	166.66		HBARC	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
20000	40.00	120.00	7.874	1.575	4.724	182.18		HBARC	*	*	*	*	*	*	*
200.00	44.00	112.00	7.874	1.732	4.409	185.62		HBAR	*	*					*
200.00	4400	112.00	7.874	1.732	4.409	193.65		HBARC		*					*
200.00	45.00	110.00	7.874	1.772	4.331	196.39		HBARC	*	*	*	*	*	*	*
200.00	5000	100.00	7.874	1.969	3.937	209.27		HBARC	*	*	*	*	*	*	*
<hr/>															
203.00	1.50	200.00	7.992	0.059	7.874	7.57		WELD	*				*		
203.00	1500	173.00	7.992	0.591	6.811	70.61		SEAM							*
<hr/>															
20400	200	200.00	8.031	0079	7.874	1012		WELD	*	*	*	*	*	*	*
<hr/>															
20500	250	200.00	8.071	0.098	7.874	12.68		WELD	*				*		
<hr/>															
206.00	3.00	200.00	8.110	0.118	7.874	15.25		WELD	*	*	*	*	*	*	*
<hr/>															
208.00	4.00	200.00	8.189	0.157	7.874	20.43		WELD					*		
<hr/>															
212.00	16.00	180.00	8.346	0.630	7.087	84.81		HBAR	*						
212.00	2100	170.00	8.346	0.827	6.693	108.48		HBAR	*	*	*	*	*	*	*
212.00	2100	170.00	8346	0.827	6.693	12408		HBARC	*	*	*	*	*	*	*
212.00	26.00	16000	8.346	1024	6.299	144.92		HBARC	*	*	*	*	*	*	*
21200	3100	150.00	8346	1220	5.906	151.74		HBAR	*			*			*
212.00	31.00	15000	8.346	1.220	5906	164.43		HBARC	*	*	*	*	*	*	*
212.00	3600	140.00	8.346	1.417	5.512	182.62		HBARC	*	*	*	*	*	*	*
212.00	41.00	130.00	8.346	1.614	5.118	18960		HBAR	*	*		*			*
212.00	4100	13000	8.346	1.614	5.118	199.47		HBARC	*	*	*	*	*	*	*
21200	46.00	120.00	8.346	1.811	4.724	214.99		HBARC	*	*	*	*	*	*	*
212.00	5100	110.00	8.346	2.008	4.331	229.19		HBARC	*	*	*	*	*	*	*
212.00	56.00	100.00	8.346	2205	3.937	24206		HBARC	*	*	*	*	*	*	*
<hr/>															
21600	3.00	210.00	8.504	0.118	8.268	16.00		WELD						*	
<hr/>															
219.10	2.00	21510	8.626	0.079	8.469	10.87		WELD	*	*	*	*	*	*	*
219.10	2.50	214.10	8.626	0.098	8.429	13.56		WELD	*						*
21910	2.60	213.90	8.626	0.102	8.421	14.10		WELD			*		*		
219.10	2.77	213.56	8.626	0.109	8.408	15.00	8 SCH 5	WELD		*	*				*
21910	2.90	213.30	8.626	0.114	8.398	15.70		WELD			*		*		
21910	3.00	213.10	8626	0.118	8.390	16.23		WELD	*	*	*	*	*	*	*
21910	3.20	212.70	8.626	0.126	8.374	17.30		WELD			*		*		
21910	3.76	211.58	8.626	0148	8330	20.27	8 SCH 10	WELD		*	*				*
21910	376	21158	8626	0.148	8.330	20.27	8 SCH 10	SEAM		*	*				*
21910	400	21110	8.626	0157	8.311	21.54		WELD			*		*		
21910	5.00	209.10	8.626	0.197	8.232	26.81		WELD			*		*		
219.10	600	20710	8.626	0.236	8.154	32.02		WELD			*		*		
21910	6.30	20650	8.626	0.248	8.130	33.57	8 SCH 20	WELD		*					*
21910	630	20650	8.626	0.248	8.130	33.57	8 SCH 20	SEAM			*		*		
21910	7.00	205.10	8.626	0.276	8.075	37.18		SEAM			*		*		
21910	8.18	202.74	8.626	0.322	7.982	43.20	8 SCH 40	SEAM	*	*	*	*	*	*	*
21910	8.18	20274	8.626	0.322	7.982	43.20	8 SCH 40	WELD		*	*				*
219.10	10.00	199.10	8.626	0.394	7839	52.36		SEAM			*		*		
219.10	1270	193.70	8.626	0.500	7626	65.64	8 SCH 80S	WELD		*	*				*
219.10	1270	19370	8.626	0.500	7.626	65.64	8 SCH 80S	SEAM		*	*		*		*
219.10	15.10	18890	8.626	0.594	7.437	101.39	8 SCH 100	HBARC	*	*	*	*	*	*	*
219.10	1826	182.58	8.626	0.719	7.188	116.30	8 SCH 120	HBARC	*	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316L	317L	310
METRIC			IMPERIAL			KGS/MTR	* = EX STOCK (OR MAX 213 WEEKS)								
MM	MM	MM	INCH	INCH	INCH										
219.10	20.62	177.86	8.626	0.812	7.002	127.08	8 SCH 140	HBARC	*	*	*	*	*		
219.10	22.23	174.64	8.626	0.875	6.876	134.28	8 XXS	HBARC	*	*	*	*	*		
219.10	23.01	173.08	8.626	0.906	6.814	137.72	8 SCH 160	HBARC	*	*	*	*	*		*
219.10	23.01	173.08	8.626	0.906	6.814	112.98	8 SCH 160	SEAM			*				*
224.00	22.00	180.00	8.819	0.866	7.087	120.18		HBAR	*	*		*			*
224.00	22.00	180.00	8.819	0.866	7.087	136.64		HBARC	*	*	*	*			*
224.00	27.00	170.00	8.819	1.063	6.693	143.85		HBAR				*			
224.00	32.00	160.00	8.819	1.260	6.299	166.16		HBAR	*			*			
224.00	32.00	160.00	8.819	1.260	6.299	179.64		HBARC	*		*	*			*
224.00	37.00	150.00	8.819	1.457	5.906	199.15		HBARC				*			
224.00	42.00	140.00	8.819	1.654	5.512	206.72		HBAR	*	*		*			*
224.00	42.00	140.00	8.819	1.654	5.512	217.33		HBARC	*	*	*	*			*
224.00	47.00	130.00	8.819	1.850	5.118	234.19		HBARC	*	*	*	*			*
224.00	52.00	120.00	8.819	2.047	4.724	249.71		HBARC	*	*	*	*			*
224.00	62.00	100.00	8.819	2.441	3.937	276.79		HBARC	*	*	*	*			*
235.00	22.50	190.00	9.252	0.886	7.480	129.30		HBAR			*	*			
236.00	23.00	190.00	9.921	0.906	7.480	132.48		HBAR	*	*		*			*
236.00	23.00	190.00	9.921	0.906	7.480	149.78		HBARC	*	*	*	*			*
236.00	33.00	170.00	9.921	1.299	6.693	181.16		HBAR	*			*			
236.00	33.00	170.00	9.921	1.299	6.693	195.43		HBARC	*	*	*	*			*
236.00	43.00	150.00	9.921	1.693	5.906	224.43		HBAR	*	*		*			*
236.00	43.00	150.00	9.921	1.693	5.906	235.78		HBARC	*	*	*	*			*
236.00	48.00	140.00	9.921	1.890	5.512	253.95		HBARC	*	*	*	*			*
236.00	53.00	130.00	9.921	2.087	5.118	270.81		HBARC	*	*	*	*			*
236.00	63.00	110.00	9.921	2.480	4.331	300.54		HBARC	*	*	*	*			*
240.00	35.00	170.00	9.44	1.378	6.693	194.03		HBAR	*						
248.00	24.00	200.00	9.764	0.945	7.874	145.39		HBAR						*	
250.00	25.00	200.00	9.843	0.984	7.874	152.12		HBAR	*	*	*	*			*
250.00	25.00	200.00	9.843	0.984	7.874	170.11		HBARC	*	*	*	*			*
250.00	35.00	180.00	9.843	1.378	7.087	218.41		HBARC	*	*	*	*			*
250.00	40.00	170.00	9.843	1.575	6.693	240.58		HBARC	*	*	*	*			*
250.00	45.00	160.00	9.843	1.772	6.299	261.42		HBARC	*	*	*	*			*
250.00	50.00	150.00	9.843	1.969	5.906	280.92		HBARC	*	*	*	*			*
250.00	50.00	150.00	9.843	1.969	5.906	270.43		HBAR							*
250.00	60.00	130.00	9.843	2.362	5.118	315.96		HBARC	*	*	*	*			*
254.00	2.00	250.00	10.000	0.079	9.843	12.62	10 OD X .079	WELD	*	*	*	*	*	*	*
255.00	2.50	250.00	10.039	0.098	9.843	15.81		WELD	*			*			
256.00	3.00	250.00	10.079	0.118	9.843	19.01		WELD	*	*	*	*	*	*	*
257.00	28.50	200.00	10.118	1.122	7.874	193.66		HBARC	*	*	*	*	*	*	*
257.00	38.50	180.00	10.118	1.516	7.087	241.97		HBARC	*	*	*	*	*	*	*
257.00	43.50	170.00	10.118	1.713	6.693	264.13		HBARC	*	*	*	*	*	*	*
257.00	48.50	160.00	10.118	1.909	6.299	284.97		HBARC	*	*	*	*	*	*	*
257.00	53.50	150.00	10.118	2.106	5.906	304.47		HBARC	*	*	*	*	*	*	*
257.00	63.50	130.00	10.118	2.500	5.118	339.51		HBARC	*	*	*	*	*	*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
267.00	8.80	249.40	10.512	0.346	9.819	56.89		SEAM		*					
267.00	25.00	217.00	10.512	0.984	8.543	18320		HBARC	*	*	*	*			*
267.00	35.00	197.00	10.512	1.378	7.756	236.02		HBARC	*	*	*	*			*
267.00	43.50	180.00	10.512	1.713	7.087	276.73		HBARC	*	*	*	*			*
267.00	53.50	160.00	10.512	2.106	6.299	319.74		HBARC	*	*	*	*			*
267.00	63.50	140.00	10.512	2.500	5.512	357.42		HBARC	*	*	*	*			*
<hr/>															
273.10	2.00	269.10	10.752	0.079	10.594	13.58		WELD	*	*		*			*
273.10	2.60	267.90	10.752	0.102	10.547	17.61		WELD			*			*	
273.10	2.90	267.30	10.752	0.114	10.524	19.62		WELD			*			*	
273.10	3.00	267.10	10.752	0.118	10.516	20.29		WELD	*	*	*	*	*	*	*
273.10	3.20	266.70	10.752	0.126	10.500	21.63		WELD			*			*	
273.10	3.40	266.30	10.752	0.134	10.484	22.96	10 SCH 5	WELD	*	*					*
273.10	4.00	265.10	10.752	0.157	10.437	26.95		WELD			*			*	
273.10	4.19	264.72	10.752	0.165	10.422	28.21	10 SCH 10	WELD	*	*				*	*
273.10	5.00	263.10	10.752	0.197	10.358	33.57		WELD			*			*	
273.10	6.00	261.10	10.752	0.236	10.280	40.13		WELD			*				
273.10	6.35	260.40	10.752	0.250	10.252	42.41	10 SCH 20	WELD	*	*					*
273.10	9.27	254.56	10.752	0.365	10.022	61.24	10 SCH 40S	SEAM	*	*	*			*	*
273.10	9.27	254.56	10.752	0.365	10.022	61.24	10SCH40S	WELD	*	*					*
273.10	12.70	247.70	10.752	0.500	9.752	82.81	10SCH80S	WELD	*	*		*			*
273.10	12.70	247.70	10.752	0.500	9.752	82.81	10 SCH 80S	SEAM	*	*				*	*
273.10	15.09	242.92	10.752	0.594	9.564	97.49		SEAM	*						
273.10	18.26	236.58	10.752	0.719	9.314	148.21	10 SCH 100	HBARC	*	*	*	*	*	*	*
273.10	20.00	233.10	10.752	0.787	9.177	126.75		SEAM			*				
273.10	21.44	230.22	10.752	0.844	9.064	167.23	10 SCH 120	HBARC	*	*	*	*	*	*	*
273.10	21.44	230.22	10.752	0.844	9.064	135.11	10 SCH 120	SEAM			*				
273.10	25.40	222.30	10.752	1.000	8.752	190.17	10 SCH 140	HBARC	*	*	*	*	*	*	*
273.10	28.58	215.94	10.752	1.125	8.502	207.99	10 SCH 160	HBARC	*	*	*	*	*	*	*
273.10	28.58	215.94	10.752	1.125	8.502	174.99	10 SCH 160	SEAM			*				*
<hr/>															
278.00	21.00	236.00	10.945	0.827	9.291	167.88		HBARC	*	*	*	*	*	*	*
278.00	24.00	230.00	10.945	0.945	9.055	185.80		HBARC	*	*	*	*	*	*	*
278.00	29.00	220.00	10.945	1.142	8.661	214.60		HBARC	*	*	*	*	*	*	*
278.00	34.00	210.00	10.945	1.339	8.268	242.06		HBARC	*	*	*	*	*	*	*
278.00	39.00	200.00	10.945	1.535	7.874	268.21		HBARC	*	*	*	*	*	*	*
<hr/>															
288.00	25.00	238.00	11.339	0.984	9.370	199.36		HBARC	*	*	*	*	*	*	*
288.00	29.00	230.00	11.339	1.142	9.055	223.35		HBARC	*	*	*	*	*	*	*
288.00	34.00	220.00	11.339	1.339	8.661	252.15		HBARC	*	*	*	*	*	*	*
288.00	39.00	210.00	11.339	1.535	8.268	279.63		HBARC	*	*	*	*	*	*	*
288.00	44.00	200.00	11.339	1.732	7.874	305.77		HBARC	*	*	*	*	*	*	*
<hr/>															
295.00	22.50	250.00	11.614	0.886	9.843	188.86		HBARC	*	*	*	*	*	*	*
295.00	27.50	240.00	11.614	1.083	9.449	220.31		HBARC	*	*	*	*	*	*	*
295.00	32.50	230.00	11.614	1.280	9.055	250.44		HBARC	*	*	*	*	*	*	*
295.00	37.50	220.00	11.614	1.476	8.661	279.24		HBARC	*	*	*	*	*	*	*
295.00	42.50	210.00	11.614	1.673	8.268	306.70		HBARC	*	*	*	*	*	*	*
295.00	47.50	200.00	11.614	1.870	7.874	332.85		HBARC	*	*	*	*	*	*	*
<hr/>															
304.00	2.00	300.00	11.969	0.079	11.811	15.12		WELD	*	*	*	*	*	*	*
<hr/>															
305.00	2.50	300.00	12.008	0.098	11.811	18.94		WELD	*			*			



STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
30600	3.00	30000	12.047	0.118	11.811	22.76		WELD	*	*	*	*	*	*	*
306.00	23.00	260.00	12.047	0.906	10.236	206.60		HBARC	*	*	*	*	*	*	*
30600	2850	249.00	12.047	1.122	9.803	242.29		HBARC	*	*	*	*	*	*	*
306.00	33.00	240.00	12.047	1.299	9.449	27031		HBARC	*	*	*	*	*	*	*
306.00	38.00	230.00	12047	1.496	9055	30017		HBARC	*	*	*	*	*	*	*
30600	4300	22000	12.047	1.693	8.661	328.71		HBARC	*	*	*	*	*	*	*
323.90	2.00	319.90	12.752	0.079	12594	16.12		WELD		*					*
32390	2.90	31810	12752	0114	12.524	23.31		WELD			*				*
32390	3.00	31790	12.752	0.118	12.516	24.11		WELD	*	*	*	*	*	*	*
323.90	3.20	317.50	12.752	0.126	12500	25.70		WELD			*				*
323.90	4.20	31550	12.752	0.165	12.421	33.62	12 SCH 5	WELD		*	*			*	*
32390	4.57	314.76	12.752	0.180	12.392	36.54	12 SCH 10	WELD	*	*	*				*
32390	500	313.90	12.752	0.197	12.358	3993		WELD			*			*	
323.90	6.35	31120	12.752	0.250	12.252	50.49	12 SCH 20	WELD		*	*				*
32390	9.53	30484	12.752	0.375	12.002	7502	12 SCH 40S	WELD		*	*				*
323.90	953	30484	12.752	0.375	12.002	75.02	12 SCH 40S	SEAM		*	*			*	*
323.90	10.00	30390	12752	0394	11.965	78.60		SEAM			*				
323.90	10.20	303.50	12.752	0.402	11949	8012		SEAM						*	
323.90	12.70	298.50	12752	0.500	11.752	9896	12 SCH 80S	WELD		*	*				*
323.90	1270	29850	12.752	0.500	11.752	98.96	12 SCH 80S	SEAM		*	*			*	*
32390	1748	288.94	12.752	0.688	11.376	17985	12 SCH 80	HBARC	*	*	*	*	*	*	*
32390	1748	288.94	12.752	0.688	11.376	134.12	12 SCH 80	SEAM		*	*				*
323.90	2000	28390	12752	0787	11.177	152.19		SEAM						*	
323.90	21.44	281.02	12.752	0.844	11.064	208.76	12 SCH 100	HBARC	*	*	*	*	*	*	*
323.90	25.40	273.10	12.752	1.000	10.752	236.83	12 SCH 120	HBARC	*	*	*	*	*	*	*
323.90	28.58	266.74	12.752	1.125	10.502	25876	12 SCH 140	HBARC	*	*	*	*	*	*	*
323.90	28.58	266.74	12.752	1.125	10.502	211.34	12 SCH 140	SEAM		*	*				
323.90	31.80	26030	12.752	1.252	10.248	23259		SEAM			*				
323.90	33.32	257.26	12.752	1.312	10.128	290.46	12 SCH 160	HBARC	*	*	*	*	*	*	*
323.90	33.32	25726	12752	1.312	10.128	24244	12 SCH 160	SEAM			*				*
33500	25.00	285.00	13.189	0.984	11220	24287		HBARC			*				
34000	20.00	30000	13.386	0.787	11.811	20902		HBARC	*	*	*	*	*	*	*
340.00	25.00	290.00	13386	0.984	11.417	246.84		HBARC	*	*	*	*	*	*	*
340.00	3000	28000	13.386	1.181	11024	283.34		HBARC	*	*	*	*	*	*	*
340.00	35.00	27000	13.386	1.378	10.630	318.51		HBARC	*	*	*	*	*	*	*
340.00	40.00	260.00	13.386	1.575	10.236	352.35		HBARC	*	*	*	*	*	*	*
350.00	20.00	310.00	13.780	0.787	12.205	215.66		HBARC	*	*	*	*	*	*	*
350.00	25.00	300.00	13780	0.984	11.811	254.80		HBARC	*	*	*	*	*	*	*
350.00	35.00	280.00	13.780	1.378	11.024	329.13		HBARC	*	*	*	*	*	*	*
350.00	40.00	270.00	13.780	1.575	10.630	364.29		HBARC	*	*	*	*	*	*	*
350.00	45.00	260.00	13.78G	1.772	10.236	398.14		HBARC	*	*	*	*	*	*	*
355.00	2.50	350.00	13.976	0.098	13.780	22.07		WELD	*			*			
355.60	2.90	349.80	14.000	0.114	13.772	25.61		WELD			*			*	
355.60	3.00	34960	14.000	0.118	13.764	26.49		WELD		*	*			*	*
355.60	3.20	349.20	14.000	0.126	13.748	28.24		WELD			*			*	
355.60	3.96	347.68	14.000	0.156	13.688	34.87		WELD		*				*	*
355.60	4.78	346.04	14.000	0.188	13.624	41.99		WELD		*				*	*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316TI316L	310
METRIC			IMPERIAL			KGS/MTR			* = EX STOCK (OR MAX 2/3 WEEKS)					
MM	MM	MM	INCH	INCH	INCH									
355.60	6.35	342.90	14.000	0.250	13.500	55.53	14 SCH 10	WELD	*	*				*
355.60	9.52	336.56	14.000	0.375	13.250	82.50	14 SCH 40S	SEAM		●	*			*
355.60	9.52	336.54	14.000	0.375	13.250	82.58	14 SCH 40S	WELD	*					*
355.60	12.00	331.60	14.000	0.472	13.055	103.24		SEAM		●				
355.60	12.70	330.20	14.000	0.500	13.000	109.04	14 SCH 80S	SEAM		●				●
355.60	19.05	317.50	14.000	0.750	12.500	211.64	14 SCH 80	HBARC	*	*	*	*		*
355.60	23.83	307.94	14.000	0.938	12.124	250.05	14 SCH 100	HBARC	*	*	*	*		*
355.60	27.79	300.02	14.000	1.094	11.812	280.95	14 SCH 120	HBARC	*	*	*	*		*
355.60	27.79	300.02	14.000	1.094	11.812	228.11	14 SCH 120	SEAM						*
355.60	31.75	292.10	14.000	1.250	11.500	311.01	14 SCH 140	HBARC	*	*	*	*		*
355.60	35.71	284.18	14.000	1.406	11.188	340.25	14 SCH 160	HBARC	*	*	*	*		*
356.00	3.00	350.00	14.016	0.118	13.780	26.52		WELD	*			*	*	
368.00	11.00	346.00	14.488	0.433	13.622	98.33		SEAM			*			
368.00	14.20	339.60	14.488	0.559	13.370	125.80		SEAM			*			
370.00	20.00	330.00	14.567	0.787	12.992	228.93		HBARC	*	*	*	*		*
370.00	25.00	320.00	14.567	0.984	12.598	270.73		HBARC	*	*	*	*		*
370.00	30.00	310.00	14.567	1.181	12.205	311.21		HBARC	*	*	*	*		*
370.00	35.00	300.00	14.567	1.378	11.811	350.36		HBARC	*	*	*	*		*
370.00	45.00	280.00	14.567	1.772	11.024	424.68		HBARC	*	*	*	*		*
385.00	20.00	345.00	15.157	0.787	13.583	238.88		HBARC	*	*	*	*		*
385.00	27.50	330.00	15.157	1.083	12.992	304.37		HBARC	*	*	*	*		*
385.00	32.50	320.00	15.157	1.280	12.598	345.88		HBARC	*	*	*	*		*
385.00	42.50	300.00	15.157	1.673	11.811	425.51		HBARC	*	*	*	*		*
385.00	52.50	280.00	15.157	2.067	11.024	499.82		HBARC	*	*	*	*		*
406.40	3.00	400.40	16.000	0.118	15.764	30.30		WELD	*	*	*	*	*	*
406.40	3.20	400.00	16.000	0.126	15.748	32.31		WELD			*		*	*
406.40	4.19	398.02	16.000	0.165	15.670	42.20	16 SCH 5S	WELD		*				*
406.40	4.78	396.84	16.000	0.188	15.624	48.07	16 SCH 10S	WELD		*				*
406.40	6.35	393.70	16.000	0.250	15.500	63.61	16 SCH 10	WELD	*	*				*
406.40	7.92	390.56	16.000	0.312	15.376	79.03	16 SCH 20	WELD	*					
406.40	9.53	387.34	16.000	0.375	15.250	94.71	16 SCH 40S	WELD	*					
406.40	12.70	381.00	16.000	0.500	15.000	125.20	16 SCH 40	WELD	*					
406.40	21.44	363.52	16.000	0.844	14.312	266.65	16 SCH 80	HBARC	*	*	*	*		*
406.40	21.44	363.52	16.000	0.844	14.312	206.67	16 SCH 80	WELD	*					
406.40	26.19	354.02	16.000	1.031	13.938	310.62	16 SCH 100	HBARC	*	*	*	*		*
406.40	30.96	344.48	16.000	1.219	13.562	353.57	16 SCH 120	HBARC	*	*	*	*		*
406.40	36.53	333.34	16.000	1.438	13.124	402.20	16 SCH 140	HBARC	*	*	*	*		*
406.40	40.49	325.42	16.000	1.594	12.812	435.77	16 SCH 160	HBARC	*	*	*	*		*
418.00	21.50	375.02	16.457	0.846	14.764	275.37		HBARC	*	*	*	*		*
418.00	29.00	360.00	16.457	1.142	14.173	346.54		HBARC	*	*	*	*		*
418.00	34.00	350.00	16.457	1.339	13.780	392.33		HBARC	*	*	*	*		*
418.00	39.00	340.00	16.457	1.535	13.386	436.78		HBARC	*	*	*	*		*
418.00	49.00	320.00	16.457	1.929	12.598	521.72		HBARC	*	*	*	*		*
440.00	20.00	400.00	17.323	0.787	15.748	275.38		HBARC		*	*	*		*
440.00	25.00	390.00	17.323	0.984	15.354	326.47		HBARC	*	*	*	*		*
440.00	30.00	380.00	17.323	1.181	14.961	376.24		HBARC	*	*	*	*		*
440.00	40.00	360.00	17.323	1.575	14.173	471.80		HBARC	*	*	*	*		*

STAINLESS STEEL HOLLOW BAR/TUBE/PIPE

OD	WALL	ID	OD	WALL	ID	WEIGHT	DESCRIPTION	TYPE	304	304L	321	316	316Ti	316L	310
METRIC			IMPERIAL			KGS/MTR			• = EX STOCK (OR MAX 2/3 WEEKS)						
MM	MM	MM	INCH	INCH	INCH										
440.00	50.00	340.00	17.323	1.969	13.386	562.03		HBARC	•	•	•	•	•	•	•
456.00	3.00	450.00	17.953	0.118	17.717	34.03		WELD	•					*	
457.20	3.00	451.20	18.000	0.118	17.764	34.12		WELD							*
457.20	4.78	447.64	18.000	0.188	17.624	54.15		WELD							*
457.20	6.35	444.50	18.000	0.250	17.500	71.69	18 SCH 10	WELD		*	*				*
457.20	23.83	409.54	18.000	0.938	16.124	327.79	18 SCH 80	HBARC	*	*	*	*	*	*	*
457.20	29.36	398.48	18.000	1.156	15.688	385.63	18 SCH 100	HBARC	*	*	*	*	*	*	*
457.20	34.93	387.34	18.000	1.375	15.250	442.24	18 SCH 120	HBARC	*	*	*	*	*	*	*
457.20	39.67	377.86	18.000	1.562	14.876	489.12	18 SCH 140	HBARC	*	*	*	*	*	*	*
457.20	45.24	366.72	18.000	1.781	14.438	542.68	18SCH 160	HBARC	*	*	*	*	*	*	*
506.00	3.00	500.00	19.921	0.118	19.685	37.79		WELD	*					*	
508.00	3.00	502.00	20.000	0.118	19.764	37.94		WELD		*					*
508.00	6.35	495.30	20.000	0.250	19.500	79.76	20 SCH 10	WELD		*	*				*
508.00	20.63	466.74	20.000	0.812	18.376	328.14	20 SCH 60	HBARC	*	*	*	*	*	*	*
508.00	26.19	455.62	20.000	1.031	17.938	394.73	20 SCH 80	HBARC	*	*	*	*	*	*	*
508.00	32.54	442.92	20.000	1.281	17.438	468.76	20 SCH 100	HBARC	*	*	*	*	*	*	*
508.00	38.10	431.80	20.000	1.500	17.000	531.83	20 SCH 120	HBARC	*	*	*	*	*	*	*
508.00	44.45	419.10	20.000	1.750	16.500	601.86	20 SCH 140	HBARC	*	*	*	*	*	*	*
508.00	50.01	407.98	20.000	1.969	16.062	661.41	20 SCH 160	HBARC	*	*	*	*	*	*	*
508.00	50.01	407.98	20.000	1.969	16.062	573.52	20 SCH 160	SEAM							*
535.00	27.50	480.00	21.063	1.083	18.898	433.47		HBARC	*	*	*	*	*	*	*
535.00	37.50	460.00	21.063	1.476	18.110	555.57		HBARC	*	*	*	*	*	*	*
535.00	47.50	440.00	21.063	1.870	17.323	672.35		HBARC	*	*	*	*	*	*	*
535.00	57.50	420.00	21.063	2.264	16.535	783.83		HBARC	*	*	*	*	*	*	*
559.00	22.23	514.54	22.008	0.875	20.257	384.33	22 SCH 60	HBARC		*	*	*	*	*	*
559.00	28.58	501.84	22.008	1.125	19.757	468.31	22 SCH 80	HBARC	*	*	*	*	*	*	*
559.00	34.93	489.14	22.008	1.375	19.257	550.13	22 SCH 100	HBARC	*	*	*	*	*	*	*
559.00	41.28	476.44	22.008	1.625	18.757	629.82	22 SCH 120	HBARC	*	*	*	*	*	*	*
559.00	47.63	463.74	22.008	1.875	18.257	707.36	22 SCH 140	HBARC	*	*	*	*	*	*	*
559.00	53.98	451.04	22.008	2.125	17.757	782.77	22 SCH 160	HBARC	*	*	*	*	*	*	*
606.00	3.00	600.00	23.858	0.118	23.622	45.30		WELD	*					*	
608.00	4.00	600.00	23.937	0.157	23.622	60.50		WELD	*					*	
609.60	24.61	560.38	24.000	0.969	22.062	455.82	24 SCH 60	HBARC	*	*	*	*	*	*	*
609.60	30.96	547.68	24.000	1.219	21.562	547.52	24 SCH 80	HBARC	*	*	*	*	*	*	*
609.60	38.89	531.82	24.000	1.531	20.938	659.02	24 SCH 100	HBARC	*	*	*	*	*	*	*
609.60	46.02	517.56	24.000	1.812	20.376	756.43	24 SCH 120	HBARC	*	*	*	*	*	*	*
609.60	52.37	504.86	24.000	2.062	19.876	840.90	24 SCH 140	HBARC	*	*	*	*	*	*	*
609.60	59.54	490.52	24.000	2.344	19.312	933.71	24 SCH 160	HBARC	*	*	*	*	*	*	*

Tolerances for Tube and Pipe

	OD	WALL
DIN 2462/2464	D1 = +/- 1.5% (min +/- 0.75mm) D2 = +/- 1% (min +/- 0.5mm) D3 = +/- 0.75% (min +/- 0.3mm) D4 = +/- 0.5% (min +/- 0.1 mm)	T1 = +/- 15% (min!: 0.6mm) T2 = +/- 12.5% (min!: 0.4mm) T3 = +/- 10% (min!: 0.2mm) T4 = +/- 7.5% (min!: 0.15mm)
ASTM A269	< 12.7mm = +/- 0.13mm ~ 12.7 < 38.1mm = +/- 0.13mm ~ 38.1 < 88.9mm = +/- 0.25mm ~ 88.9 < 139.7mm = +/- 0.38mm ~ 139.7 < 203.2mm = +/- 0.76mm	+/- 15% +/- 10% +/- 10% +/- 10% +/- 10%
ASTM A312/A530	10.29 < 48.26mm = +OAO/-0.80mm > 48.26 < 114.3mm = +0.80/-0.80mm > 114.3 < 219.1 mm = +1.60/-0.80mm > 219.1 < 457.2mm = +2AO/-0.80mm > 457.1 < 660.2mm = +4.00/-0.80mm	+ not specified / -12.5% + not specified / -12.5% + not specified / -12.5% + not specified / -12.5% + not specified / -12.5%
ASTM A511 (hot finished)		

O.D. (mm)	Ratio Wall: O.D.	O.D. AND WALL THICKNESS TOLERANCE				
		O.D. (mm)	WALL THICKNESS (%)			
			< 2.77	2.77 -- 4.37	4.38 -- 5.15	> 5.15
< 76.1 excl.	---	+ / - 0.58	+/-16.5	+/-15	+ / - 14	+ / -12.5
76.1 -- 139.7 axcl.	---	+ / - 0.79	+ / - 16.5	+/-15	+/-14	+ / - 12.5
139.7 -- 203.2 axcl.	---	+/-1.19	---	---	+ / - 14	+ / - 12.5
203.2 -- 273.1 axcl	~5%	+/-1.19	---	---	---	+ / - 12.5
273.1 -- 323.8 axcl.	<5%	+ / - 1.60	---	---	---	+ / - 12.5

Tolerances for Extruded Hollow Bar (HBAR)

OD : + 2% / - 0% with a minimum of 1mm
ID : + 0% / - 2% with a minimum of 1mm

Wall Thickness: Minimum thickness: 5% below nominal thickness
Maximum thickness: No limit

Straightness : Max. 0.2% of the length, measured over the entire length. Local deviations Max. 1mm / m

Chemical Analysis for Austenitic Stainless Steel

GRADE

CHEMICAL ANALYSIS IN %

DIN	AISI uns	AFNOR	SS	C max.	Si max.	Mn max.	P max.	S max.	Cr	Ni	Mo	Ti min.	Others
1.4301	TP 304	Z6CN18'09	304 S 18	0.07 0.08	1.00	2.00	0.045	0.030	17.0' 19.0 18.0' 20.0	8.5' 11.0 8.0' 10.5			
				0.07 0.06	1.00	2.00	0.040	0.030	17.0' 19.0 17.0' 19.0	8.0' 10.0 9.0' 12.0			
1.4306	TP 304 L	Z2 CN 18' 10	304 S 14	0.03 0.03	1.00	2.00	0.045 0.045	0.030 0.030	18.0' 20.0 18.0' 20.0	10.0' 12.5 8.0' 12.0			
				0.03 0.03	1.00	2.00	0.040 0.040	0.030 0.030	17.0' 19.0 17.0' 19.0	9.0' 11.0 10.0' 13.0			
1.4401	TP 316	Z6 CND 17' 11	316 S 18	0.07 0.08	1.00	2.00	0.045	0.030	16.5' 18.5 16.0' 18.0	10.5' 13.5 10.0' 14.0	2.00' 2.50 2.00' 3.00		
				0.07 0.07	1.00	2.00	0.040	0.030	16.0' 18.0 16.0' 18.5	10.0' 12.5 11.0' 14.0	2.00' 2.50 2.00' 3.00		
1.4404	TP 316 L	Z2 CND 17' 12	316 S 14	0.03 0.03	1.00	2.00	0.045 0.045	0.030 0.030	16.5' 18.5 16.0' 18.0	11.0' 14.0 10.0' 14.0	2.00' 2.50 2.00' 3.00		
				0.03 0.03	1.00	2.00	0.040 0.040	0.030 0.030	16.0' 18.0 16.0' 18.5	10.5' 13.0 12.0' 15.0	2.00' 2.50 2.00' 3.00		
1.4435				0.03	1.00	2.00	0.045	0.030	16.5' 18.5	12.5' 15.0	2.50' 3.00		
For corresponding grades refer to DINW.nR 1.4404													
1.4436				0.07	1.00	2.00	0.045	0.030	16.5' 18.5	11.0' 14.0	2.50' 3.00		
For corresponding grades refer to DINW.nR 1.4401													
1.4541	TP 321	Z6 CNT 18' 10	321 S 18	0.08 0.08	1.00	2.00	0.045	0.030	17.0' 19.0 17.0' 19.0	9.0' 12.0 9.0' 12.0		5 x % C max. 0.8 5x%C	
				0.08 0.08	1.00	2.00	0.040	0.030	17.0' 19.0 17.0' 19.0	9.0' 11.0 10.0' 13.0		5 x % C max. 0.6 5 x % C max. 0.6	
1.4550	TP 347	Z6 CNNb 18' 10	347 S 18	0.08 0.08	1.00	2.00	0.045	0.030	17.0' 19.0 17.0' 20.0	9.0' 12.0 9.0' 13.0			Nb : 10x% Cmax.1.00 Nb + Ta : 10x% Cmax.1.00
				0.08 0.08	1.00	2.00	0.040	0.030	17.0' 19.0 17.0' 19.0	9.0' 11.0 9.0' 12.0			Nb + Ta : 10 x % C max. 1.00 Nb + 10 x % C : 1.00or20x%C
1.4571	TP 316 Ti	Z6 CND 17' 12	320 S 17	0.08 0.08	1.00	2.00	0.045	0.030	16.5' 18.5 16.0' 18.0	11.0' 14.0 10.0' 14.0	2.0' 2.50 2.00' 3.00	5x%C 5x%C	
				0.08 0.03	1.00	2.00	0.040	0.030	16.0' 18.0 16.5' 18.5	10.5' 13.0 11.0' 14.0	2.00' 2.50 2.25' 3.00	5 x % C max. 0.6 4 x % C max. 0.6	